



Ref. No.: REC/CED/12.07.23/07

Date: 12/07/2023

TEST REPORT

Departmental Consultancy No.- CE/831

Sample: Cement Concrete Cube

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division-Baharaich (U.P.).

Name of Work: जनपद श्रावस्ती के न्यायालय परिसर में 144 नग अधिवक्ता चैम्बर का निर्माण कार्य।

Reference: 29/बहो/यू०पी०आर०एन०एस०एस०/2023-24, Dated: 11.05.2023

Tested for: Compressive Strength

Tested as per: IS 456:2000, IS 516:1959


No. of Sample: One set only.


TEST RESULTS


Specimen No.	Age (Days)	Crushing Load (kN)	Area (mm ²)	Compressive Strength (N/mm ²)	Average Compressive Strength
1.	28	625	22500	27.78	27.56
2.	28	610	22500	27.11	
3.	28	625	22500	27.78	

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Anupam Kumar Verma)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator