



**TEST REPORT**

Departmental Consultancy No.- CE/831

Sample: Fine Aggregate (Coarse Sand)

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division-Baharaich (U.P.).

Name of Work: जनपद श्रावस्ती के न्यायालय परिसर में 144 नग अधिवक्ता चैम्बर का निर्माण कार्य।

Reference: 29/बह0/यू0पी0आर0एन0एस0एस0/2023-24, Dated: 11.05.2023

Tested for: Sieve Analysis & Fineness Modulus

Tested as per: IS:2386 (Part-I)- 1963

No. of Sample: One no. of Fine Aggregate

Identification Mark: N/A


**TEST RESULTS**

**Fine Aggregate (Coarse Sand)**

| S. No. | I.S. Sieve Designation  | % Passing by Weight |
|--------|-------------------------|---------------------|
| 1.     | 10 mm                   | 100.0               |
|        | 4.75 mm                 | 97.3                |
|        | 2.36 mm                 | 89.6                |
|        | 1.18 mm                 | 83.4                |
|        | 600 microns             | 71.2                |
|        | 300 microns             | 34.1                |
|        | 150 microns             | 3.7                 |
| 2.     | Fineness Modulus = 2.21 |                     |

**Conditions:**

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.

  
(Anupam Kumar Verma)  
Lab. Staff

  
(Amit Kumar Rai)  
Co-Principal Investigator

  
(Avaneesh Kr. Yadav)  
Principal Investigator