



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

TEST REPORT

Departmental Consultancy No.- CE/669

Sample: Burnt Clay Brick

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Division-Baharaich (U.P.).

Name of Work: 144 नग अधिवक्ता चैम्बर श्रावस्ती का निर्माण कार्य।

Reference: 589 / बहो / यू०पी०आर०एन०एस०एस० / 2022-23/gh-31, Dated: 24.01.2023

Tested for: Physical Properties

Tested as per: IS 1077:1992, IS 3495:1992, IS 5454:1976

No. of Sample: One set only.


Identification Mark: भारत

TEST RESULTS

Sr. No.	Frog Mark	Examination of General Quality	Average Compressive Strength (N/mm ²)
1.	भारत	The bricks are free from cracks & flaws, have smooth rectangular faces with sharp corners, are uniform in colour.	17.03

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Pooja Pathak)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator