

To

No 28742/Distt. Lab P.W.D/MBD.

Laboratory Sample No:- प्रपत्र नं १ (१०९)

Name of Material :- Bricks (K F C mark)

Submitted By :- सहा. अनिल कुमार शर्मा नि.सह. २०१५. नि.सह. मुसादाबाद

Vide Letter No. ५७७ / डा. अरुण कुमार शर्मा, पं. बि. २०१६-१७ दिनांक १७-१०-२०१८

Location used or to be used :- राजकीय महिला शैक्षणिक अकादमी, मुंबई, महाराष्ट्र

Examination for :- Compressive Strength of Bricks.

RESULTS :- 5 Bricks Main Value Tiles Av.

Sl.No.	Name of Tests	Results
1-	Mean Value Compressive Strength of Bricks.	= 152.17 kg/cm ²

REMARKS :-

- (i) The results pertain to submitted samples only.
- (ii) The sample shall be destroyed after Testing or some simple one month form the date of dispatch of the report.
- (iii) The sample have consumed during testing.

28/11/2016
Lab Assistant
Dist.-Lab C.D. 1
P.W.D. Moradabad

Assistant Engineer (Law)
C.D. 1 P.W.D.,
Moradabad

