



इंस्टीट्यूट ऑफ इंजीनियरिंग एण्ड टेक्नोलॉजी
सीतापुर रोड, लखनऊ - 226021 (उ.प्र.) भारत
INSTITUTE OF ENGINEERING & TECHNOLOGY
Sitapur Road, Lucknow-226021 (U.P.) India
CIVIL ENGINEERING DEPARTMENT

IET/CE/JBS/Testing/2022-1105

Date: 02.02.2022

To:


Superintending Engineer,
UPRNSS, Const. Div. 3
5/148, Vikas Nagar,
Lucknow

Dear Sir,

Kindly refer your letter No. UPRNSS NI PRA L-III/1574 Dated 09.12.21 regarding testing of materials of under construction of Ramp at Court, Barabanki. The test results follows:

1. Average Compressive Strength of Brick : 15.4 N/mm²
2. Average Compressive Strength of Cube : 24.8 N/mm²
3. Steel :

	Unit	8 mm	10mm	12mm
Tensile Strength	N/mm ²	565.50	569.50	568.20


(Er. B. K. Agrawal)
Senior Instructor


(Dr. J.B. Srivastava)
Prof. & PI