



Rajkiya Engineering College Ambedkar Nagar (U.P.) - 224122
Department of Civil Engineering

Ref. No.: REC/CED/200822/02

Date: 20/08/2022

TEST REPORT

Departmental Consultancy No.- CE/457

Sample: Burnt Clay Brick

Source of Sample: Executive Engineer, U.P.R.N.S.S. Ltd., Construction Division-Gonda-I
Gonda (U.P.).

Name of Work: जनपद बलरामपुर में ग्राम बंजरिया विकास खंड गैण्डास बुजुर्ग में निर्माणाधीन राजकीय महिला आई०टी०आई०
का निर्माण कार्य।

Reference: 423/उ०प्र०रा०नि०स०स०/गोण्डा/सा०परी०/22-23, दिनांक / Dated: 14.07.2022

Tested for: Physical Properties

Tested as per: IS 1077:1992, IS 3495:1992, IS 5454:1976

No. of Sample: One set only.


Identification Mark: K.B.F.


TEST RESULTS


Sr. No.	Frog Mark	Examination of General Quality	Average Compressive Strength (N/mm ²)	Water Absorption (% of oven dried mass)	Efflorescence
1.	K.B.F.	The bricks are free from cracks & flaws, have smooth rectangular faces with sharp corners, are uniform in colour.	15.23	11.94	Slight

Conditions:

- 1) Results given above refer only to the sample(s) supplied. Since the representative sample has not been taken in our presence, we don't take any responsibility regarding the quality of bulk material from which the sample was sent for testing in the laboratory.
- 2) The report in full or in any part should not be published, advertised, photocopied or used for any legal action unless prior permission has been obtained from the Director, REC, Ambedkar Nagar.
- 3) This report is being issued on the specific understanding that REC, Ambedkar Nagar will in no way be involved in any action following the interpretation of the above results.


(Anupam Kumar Verma)
Lab. Staff


(Amit Kumar Rai)
Co-Principal Investigator


(Avaneesh Kr. Yadav)
Principal Investigator

