

TEST REPORT

Ref. No: 1030-1/NIEL/UPRNS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/ Sample : Burnt Clay Bricks

Sample Received On : 11.11.2025

Date of Start of Test : 12.11.2025

Date of Completion of Test : 17.11.2025

TEST RESULT OF BURNT CLAY BRICKS

1. Compressive Strength Test of Burnt Clay Bricks:

Serial No.	Identification Marks on the Specimen	Dimension of the Specimen			C.S. Area of the Specimen (mm ²)	Max. Load Applied (kN)	Compressive Strength (N/mm ²)	Avg. Compressive Strength (N/mm ²)
		Length (mm)	Width (mm)	Height (mm)				
1	VIJAY	230	108	70	24840.00	388.7	15.65	16.2
2	VIJAY	228	109	69	24852.00	422.9	17.02	
3	VIJAY	230	109	70	25070.00	404.1	16.12	
4	VIJAY	229	111	69	25419.00	391.8	15.41	
5	VIJAY	230	110	70	25300.00	419.0	16.56	

Test Reference:- IS: 3495 (Part 1) - 2019

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. The test samples will be disposed after one month from the date of completion of test unless otherwise specified.
4. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
5. The Company shall not be responsible for giving any legal defense/opinion for appearing in a court of law in connection with the report/test results submitted.
6. All disputes subject to Prayagraj Jurisdiction only.

Issued/Approved By:

(Er. Vikarsh Tiwari)

(Authorized Signatory)

Director

End of Report

Page- 01 of 01

TEST REPORT

Ref. No: 1030-2/NIEL/UPRNSS/2025

Date: 19/11/2025

Client : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Client's Add. : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025
Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj
Material : Sand **Sample Received On** : 11.11.2025
Type : Coarse **Date of Start of Test** : 13.11.2025
Date of Completion of test : 16.11.2025

TEST RESULTS OF COARSE SAND

1. Sieve Analysis/ Gradation Test of Sand:

Serial No.	I.S. Sieve Size (mm)	Weight Retained (gm)	Cumulative Wt. Retained (gm)	Cumulative %age Weight Retained	Cumulative %age Passing	Required %age Passing for Gr-II
1	10	0.0	0.0	0.0	100	100
2	4.75	37.2	37.2	7.4	93	90 to 100
3	2.36	59.9	97.1	19.4	81	75 to 100
4	1.18	85.1	182.2	36.4	64	55 to 90
5	0.600	114.5	296.7	59.3	41	35 to 59
6	0.300	136.2	432.9	86.6	13	8 to 30
7	0.150	48.7	481.6	96.3	4	0 to 10
Σ Cumulative %age Weight Retained				305.54	F.M.	3.06

Test Ref:- IS: 2386 (Part-I)-1963, Reaffirmed 2021 & IS: 383-2016

Wt. of Sample Taken: 500gms

Confirming to Grading Zone (As per above Gradation) : II

2. Silt Content: As Per IS: 2386 (Part-II)-1963, Reaffirmed 2021 : 0.67%

Remarks: (i) Sample was submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied sample only.

Checked By

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

- The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
- The test samples will be disposed after one month from the date of completion of test unless otherwise specified.
- This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
- The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
- All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 01 of 01

Issued & Approved By

 (Utkarsh Tiwari)
 Authorized Signatory
 Director

TEST REPORT

Ref. No: 1030-3/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/Sample : Cement Mortar

Proportion : Cement : Sand

Sample Received On : 11.11.2025

TEST RESULT OF CEMENT MORTAR


1. Dry Mortar Test:

Sr. No.	Wt. of Dehydrated Sample (Ws) (gms)	Wt. of Sample after Acid Wash (Wsa) (gms)	Fine Aggregate (Af) = $(Wsa/Ws) \times 100$ (%)	Cement (Ct) = $(100-Af)$ (%)	Mortar Ratio (Cement: Fine Aggregate)	Avg. Value of Mortar Ratio (Cement: Fine Aggregate)
1	10.00	7.99	79.90	20.10	1 : 3.97	1 : 4.02
2	10.00	8.02	80.20	19.80	1 : 4.05	
3	10.00	8.01	80.10	19.90	1 : 4.03	

Test Reference:- ASTM: C1324-15

Remarks: (i) Sample was submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied sample only.

Checked By


(Dinesh Kumar Soni)

Lab In-Charge

Notes:

- The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
- The test samples will be disposed after one month from the date of completion of test unless otherwise specified.
- This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
- The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted
- All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page 01 of 01

Issued & Approved By

(Dr. Utkarsh Tiwari)
(Authorized Signatory)
Director

TEST REPORT

Ref. No: 1030-4/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025
: Construction Work of Public Health Unit in Karchana in District Prayagraj
Material/Sample : TMT Steel Bars
Brand / Make : GALLANTT
Grade of Steel : Fe-550D

Sample Received On : 11.11.2025
Date of Start of Test : 14.11.2025
Date of Completion of Test : 18.11.2025


TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia. (mm)	Identification Mark on Steel Bar Specimen	Yield Stress (N/mm ²)	Avg. Yield Stress (Mpa)	Ultimate Tensile Strength (N/mm ²)	Avg. Ultimate Tensile Strength (Mpa)	%age Elongation
1	8	GALLANTT-TMT-550D	570.9	568	667.1	670	22.0
2	8		565.1		672.8		20.0
3	8		569.4		670.6		22.5

Relevant Code:- IS: 1608 -2022

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:


19.11.2025

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 01 of 02

Issued/Approved By:

19/11/2025
(Utkarsh Tiwari)
(Authorized Signatory)
Director

TEST REPORT

Ref. No: 1030-4/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/Sample : TMT Steel Bars

Sample Received On : 11.11.2025

Brand / Make : GALLANTT

Date of Start of Test : 14.11.2025

Grade of Steel : Fe-550D

Date of Completion of Test : 18.11.2025


TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia.(mm)	Identification Mark on Steel Bar Specimen	Cross Sectional Area (mm ²)	Nominal Mass (kg/mtr.)	Bend Test	Rebend Test
1	8	GALLANTT-TMT-550D	50.24	0.394	OK	OK
2	8		50.33	0.395	OK	OK
3	8		50.29	0.395	OK	OK

Relevant Code:- IS: 1599-2019 & IS: 1786-2008, Reaffirmed 2018

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:



(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 02 of 02

Issued/Approved By:

(Dr. Utkarsh Tiwari)
(Authorized Signatory)
Director

TEST REPORT

Ref. No: 1030-5/NIEL/UPRNSS/2025

Date: 19.11.2025


Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj
Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj
Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025
Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj
Material/Sample : TMT Steel Bars Sample Received On : 11.11.2025
Brand / Make : GALLANTT Date of Start of Test : 14.11.2025
Grade of Steel : Fe-550D Date of Completion of Test : 18.11.2025

TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia. (mm)	Identification Mark on Steel Bar Specimen	Yield Stress (N/mm ²)	Avg. Yield Stress (Mpa)	Ultimate Tensile Strength (N/mm ²)	Avg. Ultimate Tensile Strength (Mpa)	%age Elongation
1	10	GALLANTT-TMT-550D	574.3	578	686.0	684	19.5
2	10		578.1		681.9		21.5
3	10		581.7		683.4		20.0

Relevant Code:- IS: 1608 -2022

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By: 
(Dinesh Kumar Soni)
Lab In-Charge

Issued/Approved By: 
(Dr. Utkarsh Tiwari)
(Authorized Signatory)
Director

Notes:

- The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
- This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
- The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
- All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 01 of 02

TEST REPORT

Ref. No: 1030-5/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/Sample : TMT Steel Bars **Sample Received On** : 11.11.2025

Brand / Make : GALLANTT **Date of Start of Test** : 14.11.2025


Grade of Steel : Fe-550D **Date of Completion of Test** : 18.11.2025

TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia.(mm)	Identification Mark on Steel Bar Specimen	Cross Sectional Area (mm ²)	Nominal Mass (kg/mtr.)	Bend Test	Rebend Test
1	10	GALLANTT-TMT-550D	78.59	0.617	OK	OK
2	10		78.66	0.617	OK	OK
3	10		78.50	0.616	OK	OK

Relevant Code:- IS: 1599-2019 & IS: 1786-2008, Reaffirmed 2018

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.

Issued/Approved By:

(Er. Ekarsh Tiwari)
Authorized Signatory
Director

End of Report

Page- 02 of 02

TEST REPORT

Ref. No: 1030-6/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj
Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025
Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj
Material/Sample : TMT Steel Bars **Sample Received On** : 11.11.2025
Brand / Make : GALLANTT **Date of Start of Test** : 14.11.2025
Grade of Steel : Fe-550D **Date of Completion of Test** : 18.11.2025


TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia. (mm)	Identification Mark on Steel Bar Specimen	Yield Stress (N/mm ²)	Avg. Yield Stress (Mpa)	Ultimate Tensile Strength (N/mm ²)	Avg. Ultimate Tensile Strength (Mpa)	%age Elongation
1	12	GALLANTT-TMT-550D	575.2	575	669.7	672	23.5
2	12		571.8		674.4		20.5
3	12		579.1		672.0		24.0

Relevant Code:- IS: 1608 -2022

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:



(Dinesh Kumar Soni)

Lab In-Charge

Notes:

- The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
- This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
- The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
- All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 01 of 02

Issued/Approved By:



(Dr. Utkarsh Tiwari)
(Authorized Signatory)
Director

TEST REPORT

Ref. No: 1030-6/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/Sample : TMT Steel Bars **Sample Received On** : 11.11.2025

Brand / Make : GALLANTT **Date of Start of Test** : 14.11.2025

Grade of Steel : Fe-550D **Date of Completion of Test** : 18.11.2025

TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia.(mm)	Identification Mark on Steel Bar Specimen	Cross Sectional Area (mm ²)	Nominal Mass (kg/mtr.)	Bend Test	Rebend Test
1	12	GALLANTT-TMT-550D	113.02	0.887	OK	OK
2	12		113.16	0.888	OK	OK
3	12		112.98	0.887	OK	OK

Relevant Code:- IS: 1599-2019 & IS: 1786-2008, Reaffirmed 2018

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By: 
 (Dinesh Kumar Soni)
 Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.

Issued/Approved By: 
 (Er. Utkarsh Tiwari)
 (Authorized Signatory)
 Director

End of Report

Page- 02 of 02

TEST REPORT

Ref. No: 1030-7/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj
Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj
Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025
Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj
Material/Sample : TMT Steel Bars **Sample Received On** : 11.11.2025
Brand / Make : GALLANTT **Date of Start of Test** : 14.11.2025
Grade of Steel : Fe-550D **Date of Completion of Test** : 18.11.2025


TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia. (mm)	Identification Mark on Steel Bar Specimen	Yield Stress (N/mm ²)	Avg. Yield Stress (Mpa)	Ultimate Tensile Strength (N/mm ²)	Avg. Ultimate Tensile Strength (Mpa)	%age Elongation
1	16	GALLANTT-TMT-550D	584.2	583	695.1	692	22.0
2	16		581.7		691.7		21.5
3	16		582.9		688.5		24.0

Relevant Code:- IS: 1608 -2022

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:



(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.



Issued/Approved By:



(Dr. Utkarsh Tiwari)
(Authorized Signatory)

Director

End of Report

Page- 01 of 02

TEST REPORT

Ref. No: 1030-7/NIEL/UPRNSS/2025

Date: 19.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhand, Prayagraj

Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/Sample : TMT Steel Bars

Sample Received On : 11.11.2025

Brand / Make : GALLANTT

Date of Start of Test : 14.11.2025

Grade of Steel : Fe-550D


Date of Completion of Test : 18.11.2025

TEST RESULTS OF TMT STEEL BARS

Serial No.	Nominal Dia.(mm)	Identification Mark on Steel Bar Specimen	Cross Sectional Area (mm ²)	Nominal Mass (kg/mtr.)	Bend Test	Rebend Test
1	16	GALLANTT-TMT-550D	201.22	1.580	OK	OK
2	16		200.95	1.577	OK	OK
3	16		201.13	1.579	OK	OK

Relevant Code:- IS: 1599-2019 & IS: 1786-2008, Reaffirmed 2018

Remarks: (i) Samples were submitted by Client in sealed/packed condition. (ii) Tests conducted on supplied samples only.

Checked By:

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

1. The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
3. This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
4. The Company shall not be responsible for giving any legal defence/opinion for appearing in a court of law in connection with the report/test results submitted.
5. All disputes subject to Prayagraj Jurisdiction only.

Issued/Approved By:

(Dr. Utkarsh Tiwari)
(Authorized Signatory)
Director

End of Report

Page- 02 of 02

TEST REPORT

Ref. No: 1033H/NIEL/UPRNS/2025

Date: 22.11.2025

Client's Name : Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Client's Address : Office of the Executive Engineer, U.P.R.N.S.S., Nirman Prakhanda, Prayagraj

Client's Ref. No. : Letter No. Memo/EE/N.P.P./F-2024-25, Dated: 10.11.2025

Site/ Work : Construction Work of Public Health Unit in Karchana in District Prayagraj

Material/ Sample : Hardened Concrete Cube

Date of Casting : 25.10.2025

Date of Receiving : 22.11.2025

Date of Testing : 22.11.2025

TEST RESULT OF HARDENED CONCRETE CUBES

Compressive Strength Test of Hardened Concrete Cubes @ 28 days:

Serial No.	Identification Mark on the CC Cubes	Weight of Specimen (Kg.)	Dimension of Concrete Cube Specimen (L x B x H) (mm)	C.S. Area of the Specimen (mm ²)	Max. Load Applied (kN)	Compressive Strength (N/mm ²)	Avg. Compressive Strength (MPa)
1	Mark-1	8.097	150.0 x 150.2 x 149.8	22530.00	543.3	24.1	24.5
2	Mark-2	8.232	150.2 x 150.4 x 150.0	22590.08	564.1	25.0	
3	Mark-3	8.170	149.8 x 150.8 x 150.2	22589.84	551.9	24.4	
Type of Machine : Digital/Automatic			Capacity : 2000kN		Date of Calibration : 05.06.2025		

Curing Condition: Field

Appearance of Fractured Faces of Concrete & Type of Fracture: Satisfactory

Test Reference:- IS: 516 (Part 1/Sec 1:2021)

Remarks: (i) Cube Specimens were brought in the lab at 28 days in wet condition (ii) Details of Specimens & site were provided by the Client/Contractor.

Checked By:

(Signature)
22.11.2025

(Dinesh Kumar Soni)

Lab In-Charge

Notes:

- The results listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
- The maximum liability of the lab is limited to the total amount charged-expenditure on the project.
- This report should not be used wholly or in parts for techno-legal purposes and in any advertising media.
- The Company shall not be responsible for giving any legal defense/opinion for appearing in a court of law in connection with the report/test results submitted.
- All disputes subject to Prayagraj Jurisdiction only.

End of Report

Page- 01 of 01

Issued/Approved By:
(Signature)
22.11.2025
(Er. Utkarsh Tiwari)
(Authorized Signatory)
Director