

GOVT. POLYTECHNIC GHAZIABAD U.P.

CIVIL ENGG. DEPTT. CONSULTANCY DIVISION TESTING REPORT

Ref No. 340/civil Engg/2025-26

Date 20/05/2025

NAME OF DEPARTMENT आमलिय इन्जिनियरी इन्जिनियरिंग डिपार्टमेंट
फिलीज गुरुकुल-गान्धिमार्ग

NAME OF THE TEST Compressive strength of M-20 (1:1½:2)

(Grouted floor) Cement concrete cube after 7 days curing.

REF. NO. Mern/इंजीरिंग इन्जिनियरिंग डिपार्टमेंट/गान्धिमार्ग/2025-26/दिनांक 02/05/25

Date casting-02/05/25 (Raft and column upto b.l.)

S. No.	NAME OF SPEC.	NAME OF TEST	RESULT	SITE DETAILS
1.	<u>15x15x15cm³</u> <u>C.C. Cube</u>	<u>Comp. strength</u>	<u>209.90 Kg/cm²</u>	<u>जिला कारगार</u>
2.	<u>— do —</u>	<u>— do —</u>	<u>215.62 Kg/cm²</u>	<u>गान्धिमार्ग के</u>
3.	<u>— do —</u>	<u>— do —</u>	<u>218.34 Kg/cm²</u>	<u>रोडवेरी के निगम</u>
4.				<u>कार्गार</u>
5.				
6.				

Note 1-Sample Collected by your agency.
2-site details as per your letter.

LR
LAB INCHARGE
CIVIL ENGG. LAB
Lecturer Civil Engg.
Govt. Polytechnic
Ghaziabad

LR
LAB OFFICER
CIVIL ENGG.
Lecturer Civil Engg.
Govt. Polytechnic
Ghaziabad

LR
PRINCIPAL
GOVT. POLYTECHNIC
GHAZIABAD U.P.
Principal
Govt. Polytechnic
Ghaziabad

GOVT. POLYTECHNIC GHAZIABAD U.P.

CIVIL ENGG. DEPTT. CONSULTANCY DIVISION TESTING REPORT

Ref No. 312.... / Civil Engg / 2025-26 Date 08/05/2025

NAME OF DEPARTMENT कार्यालय अधिशासी अभियंता मृ. पी. आर. एन. एस. एस. निमीष प्रमोद-गाजियाबाद

NAME OF THE TEST Impact value of 20mm stone grit.

Aggregate :

REF. NO. Memo / मृ. पी. आर. एन. एस. एस. / गाजियाबाद / 2025-26 / दिनांक 08/05/25

S. No.	NAME OF SPEC.	NAME OF TEST	RESULT	SITE DETAILS
1.	20mm Stone grit	Impact value	21.35	जिला कारागार गाजियाबाद
2.	do	do	21.40	मे. डोसेरी के निर्माण
3.	do	do	21.45	रुखी /
4.				
5.				
6.				

Note 1- Sample Collected by your agency.
2- Site details as per your letter.

Ge
LAB INCHARGE
CIVIL ENCG. LAB
Lecturer Civil Engg.
Govt. Polytechnic
Ghaziabad

12
LAB OFFICER
CIVIL ENCG.
Lecturer Civil Engg.
Govt. Polytechnic
Ghaziabad

la:
PRINCIPAL
GOVT. POLYTECHNIC
GHAZIABAD U.P.
Principal
Govt. Polytechnic
Ghaziabad

CIVIL ENGG. DEPTT. CONSULTANCY DIVISION TESTING REPORT

Date... 08/05/2025

NAME OF THE TEST Compressive strength of M-150 Int.
class-bricks (B 5 S mark)

S. No.	NAME OF SPEC.	NAME OF TEST	RESULT	SITE DETAILS
1.	M-150 class brick	Comp strength	151.91 Kg/cm ²	जिला कारागार गा.
2.	— do —	— do —	152.45 Kg/cm ²	जे जेरजेशी डे
3.	— do —	— do —	153.36 Kg/cm ²	कापि
4.				
5.				
6.				

Note 1-Sample Collected-by your agency:
2-Site details as per your letter:

Principal
Govt. Polytechnic
Ghaziabad U.P.

GOVT. POLYTECHNIC GHAZIABAD U.P.

CIVIL ENGG. DEPTT. CONSULTANCY DIVISION TESTING REPORT

Ref No. 211/civil/Engrg/2025-26

Date 02/05/2025

NAME OF DEPARTMENT अभियंता, अधिकांश इमिगना मु.पो.झारख.प-1 रां. रां.

NAME OF THE TEST Flexural Modulus of Concrete Slab

REF. NO. 211/civil/Engrg/2025-26/दिनांक-02/05/25

S. No.	NAME OF SPEC.	NAME OF TEST	RESULT	SITE DETAILS
1.	<u>Concrete Slab</u>	<u>Flexural Modulus</u>	<u>2.00</u>	<u>जिला कारागार गजियाबाद</u>
2.	<u>do</u>	<u>do</u>	<u>2.02</u>	<u>मे दोरगेशी के निगीव</u>
3.	<u>do</u>	<u>do</u>	<u>2.04</u>	<u>कार्ग</u>
4.				
5.				
6.				

Note 1- Sample Collected by your agency.
2- Site details as per your letter.

Dr
LAB INCHARGE
CIVIL ENGG. LAB
Lecturer Civil Enng.
Govt. Polytechnic
Ghaziabad

Dr
LAB OFFICER
CIVIL ENGG.
Lecturer Civil Enng.
Govt. Polytechnic
Ghaziabad

Dr
PRINCIPAL
GOVT. POLYTECHNIC
GHAZIABAD U.P.
Principal
Govt. Polytechnic
Ghaziabad

CIVIL ENGG. DEPTT. CONSULTANCY DIVISION TESTING REPORT

Date: 02/05/2025...

NAME OF THE TEST: Impact value of human stone pit

Appropriate:

REF. NO. Moam / गृ-ई-आ. एन. एन. एड. / शांतिनाथ / 2025-26 / दि-11-02/05/25

S. No.	NAME OF SPEC.	NAME OF TEST	RESULT	SITE DETAILS
1.	40mm stone grit	Insoluble Value	12.22	जिला कारागार गजियाबाद
2.	— do —	— do —	19.05	मे ओरनेशु कुमरीन
3.	— do —	— do —	19.10	राशि 1
4.				
5.				
6.				

Note 1-Sample Collected by your agency.
2-Site details as per your letter.

Principal
Govt. Polytechnic
Ghaziabad U.P.