



☎:2255551

Maharana Pratap Polytechnic

GORAKHPUR

Ref. No.

MEC/CIVIL /HWY SL1658E

Date.

20.09.2021

TESTING REPORT

Source : Executive Engineer
UPRNSS, Construction Div.
Gorakhpur First

Ref. letter No. : 906 / निर्माण / सामग्री परीक्षण / दिनांक-25.02.2021

Sample Received : Coarse Sand ,Brick ,Cement ,Cube

RESULTS

1st Coarse Sand —

Total Wt. 1000gm

Size of Sieve	Wt. retained in gm	% wt. retained	Cumulative % retained	% of passing	Grading limit for coarse sand (zone II) According to IS.383-1961
10mm	---	---	---	100	100%
4.75 mm	70	7.00	7.00	93.00	90-100%
2.36 "	69	6.7	13.7	86.3	75-100%
1.18 "	163	16.3	30.0	70.00	55-90%
600 μ	176	17.6	47.6	52.4	35-59%
300 "	362	36.2	84.8	15.20	8-30%
150 "	162	16.2	100.00	0.00	0-10%

Coarse Sand Followed Grading Zone - III

2nd Bricks

Makes	Specimen	Brick Crushing strength in kg /cm ²
STY	1 st	152.40
	2 nd	151.50
	3 rd	152.60

3rd Cement – Ultratech PPC

Sl. No.	Name of test	Results
1	Fineness	4.10%
2	Initial setting time(min)	51minutes
3	Final setting time(max)	4.30Hours



☎:2255551

Maharana Pratap Polytechnic

GORAKHPUR

Ref. No.

Date.

4th Cube

Sr.no	Sample no	Compressive Strength in N/mm ² (Mpa)after 28 days
01	1 st	22.40
	2 nd	23.50
	3 rd	22.60

Test results are for sample supplied by party mentioned.

Counter Sign.

P.singh
Principal
M.P.Polytechnic

GKP

प्रधानाचार्य

महाराणा प्रताप पॉलीटेक्निक

गोरखपुर

A.K.Agrawal

A.M.I.E. civil

Lecturer

Civil Engg. Deptt

M.P.Polytechnic ,GKP