



84

# U.P.P.W.D. DISTRICT LABORATORY, HARDOI

To, The महेश्वरी माधेयवा  
उत्तर प्रदेश राज्य विज्ञान प्रयोगशाला  
लखनऊ

No. 149/63 P.W.D./2022

Date 31/7/25

Laboratory Sample No. (149)

Name of Material Brick

Sample Submitted By महेश्वरी माधेयवा

Vide Letter No. 403/2 मी. आर. एन. एस. एम. नि. उ. लखनऊ/25-26 दिनांक 26/7/25

Location to be used पुस्तकालय द्वारा जगद एटवाटि के आगवासीद मन्त्र विनिम

Examined for Compressive strength

Bond No. x

| Sl. NO.                          | Frog. Mark | Load in Kg. | Compressive Strength Kg. / CM <sup>2</sup> |
|----------------------------------|------------|-------------|--------------------------------------------|
| 1                                | YASH       | 38367.3415  | 151.6415/cm <sup>2</sup>                   |
| 2                                | YASH       | 37959.1815  | 150.0315/cm <sup>2</sup>                   |
| 3                                | YASH       | 38163.2615  | 150.8415/cm <sup>2</sup>                   |
| 4                                | /          | /           | /                                          |
| 5                                | /          | /           | /                                          |
| Average 150.8315/cm <sup>2</sup> |            |             |                                            |

- Note :** 1- The result only pertains to the particular sample submitted for the test.  
 2- The samples submitted are Destroyed during the test.  
 3- The laboratory will not be responsible regarding the interpretation of the results.

Tested By

Lab Asst.  
District Lab

Office in Charge  
District Lab  
P.W.D. Hardoi

Copy to -

OFFICE IN CHARGE  
DISTT. LAB P.W.D. HARDOI



# U.P.P.W.D. DISTRICT LABORATORY, HARDOI

To, The कॉन्स्टीबल/अभिप्रेता  
उत्तराखण्ड राज्य विमान विभाग नंदी गी.  
विमान विभाग बलम III, बलम

Date 31/7/25

No. 147/Lab.PDPWD/15-26

Laboratory Sample No. 147

Name of Material Concrete Cube

Sample Submitted By अभिप्रेता

Vide Letter No. 403/2.जी.आ.एन.एम.ए.डि.उ.2011/15-26 दिनांक 26/07/25

Location to be used पट्टा विमान विभाग बलम III, बलम

Examined for Compressive strength

Date of Casting x

Duration days of soaking x

Date of Testing x

Mix (As per Information) उपरोक्त परीक्षण परीक्षण उपकरण का उपयोग करके किया गया

Bond No. x

| Sl. No.                         | IDENTIFICATION MARK | TOTAL CRUSHING LOAD IN N/Kg | CROSS SECTIONAL AREA IN MM <sup>2</sup> | COMPRESSIVE STRENGTH IN N/ MM <sup>2</sup> |
|---------------------------------|---------------------|-----------------------------|-----------------------------------------|--------------------------------------------|
| 1.                              | DE                  | 455.01 KN                   | 22500.0 mm <sup>2</sup>                 | 20.22 N/mm <sup>2</sup>                    |
| 2                               | ER                  | 460.0 KN                    | 22500.0 mm <sup>2</sup>                 | 20.44 N/mm <sup>2</sup>                    |
| 3                               | PE                  | 450.0 KN                    | 22500.0 mm <sup>2</sup>                 | 20.00 N/mm <sup>2</sup>                    |
| AVERAGE 20.22 N/mm <sup>2</sup> |                     |                             |                                         |                                            |

Note : 1- The result only pertains to the particular sample submitted for the test.

2- The samples submitted are Destroyed during the test.

3- The laboratory will not be responsible regarding the interpretation of the results.

Co, Dim  
sted By

Lab Asst.  
District Lab

Office in Charge  
District Lab  
P.W.D. Hardoi