

075

Lab/CD 1 PWD/2025-26

Date: 05-2-2026

TEST REPORT (COMPRESSIVE STRENGTH)

Sample Taken:- Bricks First Class

Sample Taken:- Bricks First Class (10-150)
Time of Work:- काष्ठात्मक निकाश का प्रयोग १५५६ ई. के मजदूरों के द्वारा किया गया

Site of Testing: 45-2-2026

Sample of Material collected by J.E./Incharge of work and provided for Testing.

No.	Measures of Brick Sample	Sample 1	Sample 2	Sample 3	Sample 4
1	Length (MM)	230.00	230.00		
2	Width (MM)	110.00	110.00		
3	Thickness (MM)	25300.00	25300.00		
4	Crushing Load (Newton)	272000.00	268000.00		
5	Compressive Strength (in N/MM ²)	10.75	10.59		
Total			21.34		
Average			10.67		

Average Compressive Strength = 10.67

 N/mm^2

average Compressive Strength of First class brick should not be less than 10.5 N/mm^2

OTE:-

- (1) The results only pertains to the particular sample submitted for the test.
- (2) The samples submitted are Destroyed during the test.
- (3) This Laboratory will not be responsible regarding the interpretation of the results.

I.E. (DRV Lab.)

CD-1, PWD,
Hardoi.

सहायक अभियन्ता
A.E.
CD-1, PWD.
Hardoi.

U.P.P.W.D. DIVISIONAL LABORATORY, HARDOI.

The

उत्तर प्रदेश राजम निर्माण वाटकारी संघ लि०
(मुंजीर शहर सम सम) निर्माण प्राकृतिक खनक नृली म लावक
शुक्ल निर्माण रजिस्ट्री

876

Lab/CD 1 PWD/2023-24

Date:- 05-2-2026

Reference:- 963/मुंजीर आर शहर सम सम/निर्माण ल-111/2025-26 दि० 6-01-2026

TEST REPORT (COMPRESSIVE STRENGTH)

Sample Taken:- Cement Concrete Cube (15 CmX 15 Cm/10 CmX10 Cm)	M-15 / 20 / 25 / 30
Name of Work:- काम माल मंगुप निवृत्त कला मंगुप मंगुप हरे के के मंगुप मंगुप	
Date of Testing :-	Test After :- 7 Days / 28 Days

Sample of Material collected by J.E./Incharge of work and provided for Testing.

Sample No.	Maximum Load (in Newton) (B)	X-sectional Area (Sq mm) ©	Compressive Strength=B/C	Required Compressive Strength as per Specification (After 7 Days)	Required Compressive Strength as per Specification (After 28 Days)
1	618750.00	22500.00	27.50	—	—
2	607500.00	22500.00	27.00	—	—
3	/	/	/	/	/
4	/	/	/	/	/
Total			54.50		
Average			27.25		

Average Compressive Strength = 27.25 N/MM²

NOTE:-

- (1) The results only pertains to the particular sample submitted for the test.
- (2) The samples submitted are Destroyed during the test.
- (3) This Laboratory will not be responsible regarding the interpretation of the results.

J.E. (Div. Lab.)
CD-1, PWD,
Hardoi.

A.E. अभियंता
CD-1, PWD,
Hardoi.