

Laboratory Information

Laboratory:
Technician:
Sample By

Test Standard:
Test Date:
Report Date:

Test Method:
Prep. Method.
Splitting Method

Sample Information

Structure:
Work Area
Source
Material Type:

Sample Name:
Sample Number:
Sample Date:
Elevation

Depth From
Depth To:
North
East

ASTM C535 Grading of Test Samples

Sieve Size, mm (in)		Mass of Indicated Sizes, g		
Passing	Retained on	Grading		
		1	2	3
75 (3)	63 (2 1/2)	2500 +/- 50	-	-
63 (2 1/2)	50 (2)	2500 +/- 50	-	-
50 (2)	37.5 (1 1/2)	5000 +/- 50	5000 +/- 50	-
37.2 (1 1/2)	25 (1)	-	5000 +/- 25	5000 +/- 25
25 (1)	19 (3/4)	-	-	5000 +/- 25
Total		10000 +/- 100	10000 +/- 75	10000 +/- 50

Testing Information

Selected Grading	
Initial Weight (g)	
Final Weight (g)	
Weight Loss (g)	
Weight Loss (%)	

Laboratory Comments:

Reviewed By: _____

Date:_____