

OREGON ON-SITE CONCRETE, INC

26045 SW Grahams Ferry Rd.
Sherwood, OR 97140
503.218.5050

CONCRETE MIX DESIGN

MIX DESIGN ID: **PDX 3000**

DESIGNED BY: Bryan Holland

CUSTOMER: OOC INTERNAL
PROJECT: OOC INTERNAL
PROJECT NO.: OOC INTERNAL

WEIGHT PER CUBIC YARD

	LBS	CU.FT.
ASTM-C150 TYPE I/II CEMENT (Cal Portland)	450	2.28
#3/4-4 COARSE AGGREGATE (Windsor Rock Products)	1880	11.58
FINE AGGREGATE (Windsor Rock Products)	1425	8.67
WATER	237	3.80
AIR ENTRAINED	2.5%	0.54
AIR ENTRAPPED	2.5%	0.81
TOTAL VOLUME		27.68

ADMIXTURES

Air Entrainment - **DARAVAIR® 1000**, ASTM C260

SPECIFICATIONS

WATER/CEMENT RATIO	0.52	
SLUMP	4-6	Inches
COMPRESSIVE STRENGTH @ 28 Days	3000	p.s.i.