



## Modified Phenolic Molding Compound



UL File: E59481  
Form : Granular  
Storage Life : 1 Year

## 改性酚醛樹脂成型材料



## PMC – T383J

*PMC-T383J Black Modified Phenolic is a two-stage, general purpose molding material offering excellent mold process-ability and optimized Cure cycles.*

*Typical applications include cookware handles and knobs, etc.*

Typical Physical Properties (測試項目)		Method (測試方法)		Typical Data (代表值)	
Grade		ASTM	JIS	Value	Unit
<b>General</b> (一般)	Specific Gravity(比重)	D792	K7112	1.43	---
	Water Absorption(吸水率)	D570	K6911	0.4	%
	Molding Shrinkage(收縮率)	D955	K6915	1.3	%
<b>Mechanical</b> (機械特性)	Charpy Impact(夏式衝擊強度)	D256	K7111	3.5	Kgf cm/cm <sup>2</sup>
	Izod Impact((艾式衝擊強度)	D256	K6911	3.0	Kgf cm/cm
	Flexural Strength(曲折強度)	D790	K7203	9.0	Kgf/mm <sup>2</sup>
	Tensile Strength(引張強度)	D651	K6911	5.5	Kgf/mm <sup>2</sup>
	Compressive Strength(壓縮強度)	D695	K6911	20	Kgf/mm <sup>2</sup>
	Deflection Temp.(熱變形溫度)	D648	K7207	155	°C
<b>Electrical</b> (電氣特性)	Dielectric Strength(耐電壓)	D149	K6915	9	KV/mm
	Insulation Resistance-N(常態絕緣)	D257	K6915	10 <sup>10</sup>	Ohm
	Insulation Resistance-B(煮沸絕緣)	D257	K6915	10 <sup>8</sup>	Ohm
	Volume Resistivity(體積阻抗)	D257	K6911	10 <sup>12</sup>	Ohm-cm
<b>UL File</b> (UL 相關)	UL 94 Flame Class(耐燃)			6.0	mm/V-0
	CTI PLC Level(耐電蝕)			4	---
	D495 PLC Level(耐電弧)			6	---
	RTI(相對熱指數)			150	°C

*The typical values listed are results obtained from the testing of standard specimens using the stated test procedures, with said specimens molded under controlled laboratory conditions from representative samples of the product*

Ver.1<sup>st</sup> /2012