



CARBON STEEL, ALLOY STEEL, LOW TEMP, PIPE AND TUBES SPECIFICATION

CHEMICAL ANALYSIS									MECHANICAL PROPERTIES			SPECIFIC REQUIREMENT
SPECIFICATION	WT	C%	Mn %	P % MAX	S% MAX	Si%	Cr%	Mo%	TENSILE STRENGTH Mpa	YIELD STRENGTH Mpa	ELONGATION 50mm MIN Longitudinal	
ASTM A 53/A	AW	0.25MAX	0.95MAX	0.050	0.060	-	-	-	331MIN	207MIN	36	<u>Cr</u> <u>Mo</u> <u>Cu</u> <u>Ni</u> <u>Va</u> 0.40 0.15 0.40 0.40 0.08 Five elements not to exceed 1%
ASTM A 53/B	AW	0.30MAX	1.20MAX	0.050	0.060	-	-	-	413MIN	240MIN	29.5	
ASTM A 106/A	AW	0.25MAX	0.27-0.93	0.025	0.025	0.10MIN	0.40MAX	0.15MAX	330MIN	205MIN	35/28	
ASTM A 106/B	AW	0.30MAX	0.29-1.06	0.025	0.025	0.10MIN	0.40MAX	0.15MAX	415 MIN	240MIN	30/22	
ASTM A 106/C	AW	0.35MAX	0.29-1.06	0.025	0.025	0.10MIN	0.40MAX	0.15MAX	485MIN	275MIN	30/22	
ASTM A 179	MW	0.06-018	0.27-0.63	0.048	0.048	-	-	-	325MIN	180MIN	36.0	Hardness 72 HRB Max
ASTM A 214	MW	0.18MAX	0.27-0.63	0.050	0.050	-	-	-	385MIN	180MIN	35.0	Hardness 72 HRB Max
ASTM A 192	MW	0.06-0.18	0.27-0.63	0.048	0.048	0.25MAX	-	-	325MIN	180MIN	35.0	Hardness 72 HRB Max
ASTM A 209/T1	MW	0.10-0.20	0.30-0.80	0.045	0.045	0.10-0.50	-	0.44-0.65	380MIN	205MIN	30/22	Hardness 80 HRB Max
ASTM A 209/T1a	MW	0.15-0.25	0.30-0.80	0.045	0.045	0.10-0.50	-	0.44-0.65	365MIN	195MIN	30/22	Hardness 81 HRB Max
ASTM A 209/T1B	MW	0.14MAX	0.30-0.80	0.045	0.045	0.10-0.50	-	0.44-0.65	415MIN	220MIN	30/22	Hardness 77 HRB Max
ASTM A 210/A-1	MW	0.27max	0.93max	0.048	0.058	0.10MIN	-	-	415MIN	255MIN	30/22	Hardness 79 HRB Max
ASTM A 210/C	MW	0.35MAX	0.29-1.06	0.048	0.058	0.10MIN	-	-	485MIN	275MIN	30/22	Hardness 89 HRB Max
ASTM A 213/T2	MW	0.10/0.20	0.30-0.61	0.045	0.045	0.10-0.30	0.50-0.81	0.44-0.65	415MIN	205MIN	30/22	Hardness 85 HRB Max
ASTM A 213/T5	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50MAX	4.00-6.00	0.44-0.65	415MIN	205MIN	30/22	Hardness 85 HRB Max
ASTM A 213/T11	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50-1.00	1.00-1.50	0.44-0.65	415MIN	205MIN	30/22	Hardness 85 HRB Max
ASTM A 213/T12	MW	0.15MAX	0.30-0.61	0.045	0.045	0.50MAX	0.80-1.25	0.44-0.65	415MIN	205MIN	30/22	Hardness 85 HRB Max
ASTM A 213/T22	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50MAX	1.90-2.60	0.87-1.13	415MIN	205MIN	30/22	Hardness 85 HRB Max
ASTM A 333/1	AW	0.30MAX	0.40-1.06	0.025	0.025	-	-	-	380MIN	205MIN	25/20	IMPACT AS -50F FOR 40X10J/18/14 -50F40X10J/18/14 90 HRB MAX
ASTM A 333/6	AW	0.30MAX	0.29-1.06	0.025	0.025	0.10MIN	-	-	415MIN	240MIN	30/22	
ASTM A 334/1	AW	0.30MAX	0.40-1.06	0.025	0.025	-	-	-	380MIN	205MIN	35/28	
ASTM A 334/6	MW	0.30MAX	0.29-1.06	0.025	0.025	0.10MIN	-	-	415MIN	240MIN	30/22	
ASTM A 335/P1	AW	0.10-0.20	0.30-0.80	0.025	0.025	0.10-0.50	-	0.44-0.65	330MIN	205MIN	30/22	
ASTM A 335/P2	AW	0.10-0.20	0.30-0.61	0.025	0.025	0.10-0.30	0.50-0.81	0.44-0.65	380MIN	205MIN	30/22	
ASTM A 335/P5	AW	0.15MAX	0.30-0.60	0.025	0.025	0.50MAX	4.00-6.00	0.45-0.65	415MIN	205MIN	30/22	
ASTM A 335/P9	AW	0.15MAX	0.30-0.60	0.025	0.025	0.25-1.00	8.00-10.00	0.09-1.10	415MIN	172MIN	30/22	
ASTM A 335/P11	AW	0.15MAX	0.30-0.60	0.025	0.025	0.50-1.00	1.00-1.50	0.44-0.65	415MIN	205MIN	30/22	
ASTM A 335/P12	AW	0.15MAX	0.30-0.61	0.025	0.025	0.50MAX	0.80-1.25	0.44-0.65	415MIN	205MIN	50/22	
ASTM A 335/P22	AW	0.15MAX	0.30-0.60	0.025	0.025	0.50MAX	1.90-2.60	0.87-1.13	415MIN	205MIN	30/22	
BS/3059/1/33		0.15Max	0.30-0.70	0.050	0.050	-	-	-	324-441	186MIN	25	
BS/3059/2/33		0.15MAX	0.40-0.70	0.050	0.050	0.10-0.35	-	-	324-441	186MIN	21	
BS/3059/2/45		0.12-0.18	0.90-1.20	0.035	0.035	0.10-0.35	-	-	441-560	245MIN	22	
BS/3059/2/620		0.10-0.15	0.40-0.70	0.040	0.040	0.10-0.35	0.70-1.10	0.45-0.65	441-618	235MIN	22	
DIN/17175/ST35.8		0.17MAX	0.40MIN	0.040	0.040	0.35MAX	-	-	340-441	235MIN	25	
DIN/17175/ST45.8		0.22MAX	0.45MIN	0.040	0.040	0.10-0.35	-	-	441-540	255MIN	25	
DIN/17175/15MO3		0.12-0.20	0.50-0.80	0.040	0.040	0.10-0.35	-	0.25-0.35	441-540	284MIN	21	
DIN/17175/13CrMO44		0.10-0.18	0.40-0.70	0.040	0.040	0.10-0.35	0.70-1.60	0.40-0.50	441-570	294MIN	22	
DIN/17175/10CrM910		0.15MAX	0.40-0.60	0.040	0.040	0.15-0.50	2.0-2.5	0.9-1.10	441-570	294MIN	22	
ASTM A 199/T5	MW	0.50-0.15	0.30-0.60	0.030	0.030	0.50MAX	4.00-6.00	0.45-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 199/T11	MW	0.05-0.15	0.30-0.60	0.030	0.030	0.50-1.00	1.00-1.50	0.44-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 199/T22	MW	0.05-0.15	0.30-0.60	0.030	0.030	0.50MAX	1.90-2.60	0.87-1.13	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 199/T4	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50-1.00	2.15-2.85	0.44-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 199/T7	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50-1.00	6.00-8.00	0.45-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 200/T5	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50-1.00	4.00-6.00	0.45-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 200/T11	MW	0.05-0.15	0.30-0.60	0.030	0.030	0.50-1.00	1.00-1.50	0.44-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 200/T22	MW	0.05-0.15	0.30-0.60	0.030	0.030	0.50MAX	1.90-2.60	0.87-1.13	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 200/T4	MW	0.05-0.15	0.30-0.60	0.030	0.030	0.50-1.00	2.15-2.85	0.44-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 200/T7	MW	0.15MAX	0.30-0.60	0.030	0.030	0.50-1.00	6.00-8.00	0.45-0.65	415MIN	170MIN	30/22	HARDNESS 85 HRB MAX
ASTM A 199/T9	MW	0.15MAX	0.30-0.60	0.030	0.030	0.25-1.00	8.00-10.0	0.90-1.10	415MIN	170MIN	30/22	HARDNESS 89 HRB MAX

CARBON STEEL & ALLOY STEEL PIPE DIMENSIONS ANSI B 36.10

Nominal Pipe Size		O/D	Schedule 10		Schedule 20		Schedule 30		Schedule STD		Schedule 40		Schedule 60		Schedule XS		Schedule 80		Schedule 100		Schedule 120		Schedule 140		Schedule 160		Schedule XXS				
			W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	W.T.	KG/M	
3	1/8	10.3							1.73	0.37	1.73	0.37			2.41	0.47	2.41	0.47													
6	1/4	13.7							2.24	0.63	2.24	0.63			3.02	0.80	3.02	0.80													
10	3/8	17.1							2.31	0.84	2.31	0.84			3.20	1.10	3.20	1.10													
15	1/2	21.3							2.77	1.27	2.77	1.27			3.73	1.62	3.73	1.62								4.78	1.95	7.5	2.55		
20	3/4	26.7							2.87	1.69	2.87	1.69			3.91	2.20	3.91	2.20								5.56	2.90	7.82	3.64		
25	1	33.4							3.38	2.50	3.38	2.50			4.55	3.24	4.55	3.24								6.35	4.24	9.1	5.45		
32	1 1/4	42.2							3.56	3.39	3.56	3.39			4.85	4.47	4.85	4.47								6.35	5.61	9.7	7.77		
40	1 1/2	48.3							3.68	4.05	3.68	4.05			5.08	5.41	5.08	5.41								7.14	7.25	10.2	9.56		
50	2	60.3							3.91	5.44	3.91	5.44			5.54	7.48	5.54	7.48								8.74	11.11	11.1	13.4		
65	2 1/2	73.0							5.16	8.63	5.16	8.63			7.01	11.41	7.01	11.41								9.53	14.92	14.0	20.4		
80	3	88.9							5.49	11.3	5.49	11.3			7.62	15.3	7.62	15.3								11.13	21.35	15.24	27.7		
90	3 1/2	101.6							5.74	13.57	5.74	13.57			8.08	18.63	8.08	18.63													
100	4	114.3							6.02	16.07	6.02	16.07			8.56	22.3	8.56	22.3			11.13	28.32				13.5	33.5	17.12	41.03		
125	5	141.3							6.55	21.77	6.55	21.77			9.53	30.9	9.53	30.9			12.7	40.2				15.9	49.11	19.0	57.4		
150	6	168.3							7.11	28.26	7.11	28.26			10.97	42.5	10.97	42.5			14.3	54.2				18.3	67.5	21.95	79.22		
200	8	219.1						6.35	33.3	7.0	36.8	42.5	8.18	42.5	10.31	53.1	12.7	64.6	12.7	64.5	15.1	75.92	18.3	90.4	20.6	100.9	23.0	111.27	22.23	108.0	
250	10	273.0						6.35	41.7	7.8	51.3	9.27	60.3	9.27	60.3	12.7	81.5	12.7	81.5	15.1	96.0	18.3	114.7	21.44	133.0	25.4	155	28.6	172.3	25.4	155.0
300	12	323.8						6.35	49.7	8.4	65.2	9.53	73.8	10.31	79.7	14.27	109.0	12.7	97.4	17.5	132.0	21.4	160.0	25.4	187.0	28.6	208	33.3	238.7	25.4	187.0
350	14	355.6	6.35	54.7	7.92	68.1	9.53	81.3	9.53	81.3	11.13	94.6	15.09	126.0	12.7	107.0	19.0	158.0	23.8	195.0	27.8	224.0	31.8	253.5	35.7	281					
400	16	406.4	6.35	62.6	7.92	77.9	9.53	93.3	9.53	93.3	12.7	123.0	16.66	160.0	12.7	123.0	21.44	203.0	26.2	245.0	30.9	286.0	36.53	333	40.5	366.0					
450	18	457.2	6.35	70.6	7.92	87.7	11.13	122.0	9.53	105.0	14.20	156.0	19.05	206.0	12.7	139.0	23.8	254.6	29.36	310.0	34.0	363.0	39.7	408.3	45.2	459.0					
500	20	508.0	6.35	78.5	9.53	117.2	12.7	155.1	9.53	117.2	15.09	183.0	20.62	248.0	12.7	155.1	26.2	311.0	32.5	381.0	38.1	441.0	44.4	508	50.0	564.0					
550	22	558.8	6.35	86.6	9.53	129.0	12.7	171.0	9.53	129.0			22.2	294.0	12.7	171.0	28.6	373.0	34.9	451.0	41.3	527.0	47.6	600	54.0	672.0					
600	24	610.0	6.35	94.5	9.53	141.0	14.3	210.0	9.53	141.0	17.48	255.0	24.61	355.0	12.7	187.0	30.9	442.08	38.8	547.7	46.0	640.0	52.4	720.15	59.5	808.22					
650	26	660.0	7.92	127.3	12.7	203.0			9.53	153.0					12.7	202															
700	28	711.0	7.92	137.4	12.7	218.0	15.88	272.0	9.53	165.0					12.7	218															
750	30	762.0	7.92	147.9	12.7	234.6	15.88	292.2	9.53	176.0					12.7	235															
800	32	812.8	7.92	157.9	12.7	250.6	15.88	312.0	9.53	188.2	17.48	342.0			12.7	251															
850	34	863.6	7.92	167.9	12.7	266.5	15.88	331.7	9.53	200.0	17.48	364.9			12.7	266															
900	36	914.4	7.92	176.9	12.7	282.4	15.88	352.2	9.53	212.0	19.05	420.6			12.7	282															



All Dimensions in millimeters. W.T. = Wall Thickness. KG/M = Kilograms per Meter.