

STAINLESS STEEL SEAMLESS & WELDED PIPES CHEMICAL & PHYSICAL PROPERTIES

Chemical Composition										Tensile Test				
Grade	C	Si	Mn	P Max	S Max	Cr	Mo	Ni	Other Elements	Tensile Strength kg/mm ² min	Yield Point Strength kg/mm ² min	Elongation in 2 or 50mm min% Curved strip and Tubular Specimens		
												Longitudinal		Transverse
												t ≤ 5/16in	t ≥ 5/16in	t ≤ 5/16in
TP304	0.08 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0		8.00-11.0	-	52.52	20.90	35	-	25
TP304H	0.04-0.10	0.75 max	2.0 max	0.040	0.030	18.0-20.0		8.00-11.0	-	52.52	20.90	35	-	25
TP304L	0.035 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0		8.00-13.0	-	49.46	17.34	35	-	25
TP304N	0.08 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0		8.00-11.0	N 0.10-0.16	56.10	24.61	35	-	25
TP304LN	0.035 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0		8.00-11.0	N 0.10-0.16	52.52	20.90	35	-	25
TP309S	0.08 max	0.75 max	2.0 max	0.045	0.030	22.0-24.0	0.75 Max	12.0-15.0	-	52.52	20.90	35	-	25
TP310S	0.08 max	0.75 max	2.0 max	0.045	0.030	24.0-26.0	0.75 Max	19.0-22.0	-	52.52	20.90	35	-	25
TP316	0.08 max	0.75 max	2.0 max	0.040	0.030	16.0-18.0	2.00-3.00	11.0-14.0	-	52.52	20.90	35	-	25
TP316H	0.04-0.10	0.75 max	2.0 max	0.040	0.030	16.0-18.0	2.00-3.00	11.0-14.0	-	52.52	20.90	35	-	25
TP316L	0.035 max	0.75 max	2.0 max	0.040	0.030	16.0-18.0	2.00-3.00	10.0-15.0	-	49.46	17.34	35	-	25
TP316N	0.08 max	0.75 max	2.0 max	0.040	0.030	16.0-18.0	2.00-3.00	11.0-14.0	N 0.10~0.16	56.10	24.61	35	-	25
TP316LN	0.035 max	0.75 max	2.0 max	0.040	0.030	16.0-18.0	2.00~3.00	11.0-14.0	N 0.10~0.16	52.52	20.90	35	-	25
TP317	0.08 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0	3.00~4.00	11.0-14.0	-	52.52	20.90	35	-	25
TP317L	0.035 max	0.75 max	2.0 max	0.040	0.030	18.0-20.0	3.00~4.00	11.0-15.0	-	52.52	20.90	35	-	25
TP321	0.08 max	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Ti5xC%-0.70	52.52	20.90	35	-	25
TP321H	0.04-0.10	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Ti4xC%-0.60	52.52	20.90	35	-	25
TP347	0.08 max	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Nb+TA10xC%-1.00	52.52	20.90	35	-	25
TP347H	0.04-0.10	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Nb+TA8xc%~1	52.52	20.90	35	-	25
TP348	0.08 max	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Nb+TA10xc%~1	52.52	20.90	35	-	25
TP348H	0.04-0.10	0.75 max	2.0 max	0.040	0.030	17.0-20.0		9.0-13.0	Nb+TA8xc%~1	52.52	20.90	35	-	25
TPXM-10	0.08 max	1.00 max	8.00-10.00	0.040	0.030	19.0-21.50		5.50-7.50	N0.15~0.40	63.22	35.18	35	-	25
TPXM-11	0.04 max	1.00 max	8.00-10.00	0.040	0.030	19.0-21.50		5.50-7.50	N0.15~0.40	63.22	35.18	35	-	25
A240 TP304	0.08 max	0.75 max	2.0 max	0.045	0.030	18.0-20.0	-	8.00-10.50	N0.10 Max			Class 1 : Double welded pipes & full Radiography Class 2 : Double welded no Radiography Class 3 : Single welded full Radiography Class 4 : Single welded full Radiography rootpass without addition of filler metal Class 5 : Double welded spot Radiography		
TP310S	0.08 max	0.75 max	2.0 max	0.045	0.030	24.0-26.0	-	19.0-22.0						
TP316	0.08 max	0.75 max	2.0 max	0.045	0.030	16.0-18.0	2.0-3.0	10.0-14.0	N0.10 Max					
TP316L	0.035 max	0.75 max	2.0 max	0.045	0.030	16.0-18.0	2.0-3.0	10.0-14.0	N0.10 Max					
TP317L	0.035 max	0.75 max	2.0 max	0.045	0.030	18.0-20.0	3.0-4.0	11.0-15.0	N0.10 Max					
TP321	0.08 max	0.75 max	2.0 max	0.045	0.030	17.0-19.0	-	9.0-12.0	N0.10 Max					
TP347	0.08 max	0.75 max	2.0 max	0.045	0.030	17.0-19.0	-	9.0-13.0	Cb+TA10xC/1.0					