

Synthetic Crystal Plasticity PDF

Page 1: A BCC ferritic steel CPFEM study links EBSD texture, stress-strain validation, and grain orientation statistics.

Evidence focus: material system, crystal structure, validation data.

Dislocation-Density Hardening

Page 2: The constitutive model uses dislocation density hardening, initial slip resistance, recovery, and forest hardening parameters.

Open limitation: the calibrated parameter set may not transfer across strain rates or heat treatments.