

Magnetoelastic wave in Ferromagnetic Thin-film Mediated by Dipolar Interaction

Hiroki Yoshida¹

¹ Department of Physics, Institute of Science Tokyo, Japan

E-mail: yoshida.h.9d8d@m.isct.ac.jp

Abstract. Here comes the abstract (≤ 200 words)

Submitted to: *Appl. Phys. Express*

Hello, world. Main text (≤ 3200 words and ≤ 5 figures, incl. the Title, Abstract, Main Text, Acknowledgements, References, Tables and figure captions.).

We start from the basic equations describing the magnetic dipolar interaction: Maxwell's equations. When the elastic deformation is present, the lattice deviates from its equilibrium positions \mathbf{r} to $\mathbf{R} := \mathbf{r} + \mathbf{u}(\mathbf{r}, t)$, where $\mathbf{u}(\mathbf{r}, t)$ is the displacement field. Then, the Maxwell's equations are rewritten in terms of this new coordinate as

$$\nabla_{\mathbf{R}} \cdot (\mathbf{H} + \mathbf{M}) = 0, \quad \nabla_{\mathbf{R}} \times \mathbf{H} \approx 0, \quad (1)$$

where in the second equation, the magnetostatic approximation is applied. This approximation is justified when the length scale is long enough so that the dipolar interaction is dominant. We decompose the magnetic field \mathbf{H} and the magnetization \mathbf{M} as $\mathbf{H} = \mathbf{H}_0 + \mathbf{h}(\mathbf{r}, t)$ and $\mathbf{M} = \mathbf{M}_0 + \mathbf{m}(\mathbf{r}, t)$, respectively. Here, \mathbf{H}_0 and \mathbf{M}_0 are quantities at the equilibrium under in-plane external magnetic field and parallel to each other. We consider a wave that is a propagation of small deviations from equilibrium. Assuming that the wave propagates in the direction parallel to the x axis at frequency ω and the film is uniform in the y direction, we have $\mathbf{h} = \mathbf{h}(z)e^{i(kx - \omega t)}$ and $\mathbf{m} = \mathbf{m}(z)e^{i(kx - \omega t)}$. We rewrite Eq. (1) in terms of these quantities in the original coordinate \mathbf{r} . We note that we need to pay attention to the conservation of the magnetization in a unit volume and as a result we get $\mathbf{M}(\mathbf{R}) = \mathbf{M}(\mathbf{r})/\det(J(\mathbf{r}))$, where $J(\mathbf{r})$ is a Jacobi matrix (see Supplemental Material [1] for detail). We get

$$\nabla_{\mathbf{r}} \cdot (\mathbf{h}(\mathbf{r}) + \mathbf{m}(\mathbf{r})) = \mathbf{M}_0 \cdot \nabla_{\mathbf{r}} (\nabla_{\mathbf{r}} \cdot \mathbf{u}(\mathbf{r})), \quad (2)$$

$$\nabla_{\mathbf{r}} \times \mathbf{h}(\mathbf{r}) = 0, \quad (3)$$

where $\nabla_{\mathbf{r}}$ stands for derivatives with respect to the coordinate \mathbf{r} . Because the surface of the film is also distorted as in Fig. , boundary conditions to solve these equations are also modified by the existence of \mathbf{u} as

$$h_x^{\text{in}} - h_x^{\text{out}} = M_{0,z} \frac{\partial u_z}{\partial x}, \quad (4)$$

$$h_z^{\text{in}} + m_z - h_z^{\text{out}} = M_{0,x} \frac{\partial u_z}{\partial x}, \quad (5)$$

at $z = \pm L/2$, where $h^{\text{in/out}}$ stand for the dipolar fields inside and outside of the film, respectively. Following the Green tensor method as in Ref. [2], the dipolar field

satisfying Eqs. (2) and (3) under boundary conditions (4) and (5) is given as (see Supplemental Material [1] for the detail)

$$\mathbf{h}(z) = \int_{-\frac{L}{2}}^{\frac{L}{2}} dz' (G^m(z, z') \mathbf{m}(z') + G^u(z, z') \mathbf{u}(z')), \quad (6)$$

where

$$G^m(z, z') = \begin{pmatrix} -G_P(z, z') & 0 & -iG_Q(z, z') \\ 0 & 0 & 0 \\ -iG_Q(z, z') & 0 & G_{P'}(z, z') \end{pmatrix}, \quad (7)$$

$$G^u(z, z') = \begin{pmatrix} ikM_{0,x}G_P(z, z') - kM_{0,z}G_Q(z, z') \\ 0 \\ -kM_{0,x}G_Q(z, z') - ikM_{0,z}G_{P'}(z, z') \\ 0 & -kM_{0,x}G_Q(z, z') - ikM_{0,z}G_{P'}(z, z') \\ 0 & 0 \\ 0 & -ikM_{0,x}G_{P'}(z, z') + kM_{0,z}G_{Q'}(z, z') \end{pmatrix}, \quad (8)$$

$$G_P(z, z') = \frac{k}{2} e^{-k|z - z'|}, \quad (9)$$

$$G_Q(z, z') = \text{sgn}(z - z') G_P(z, z'), \quad (10)$$

$$G_{P'}(z, z') = G_P(z, z') - \delta(z - z'), \quad (11)$$

$$G_{Q'}(z, z') = G_Q(z, z') - \frac{1}{k} \frac{\partial}{\partial z'} \delta(z - z'). \quad (12)$$

This dipolar field couples the magnetostatic wave and elastic wave on the film. We note that in the current setup, there are no couplings when the equilibrium magnetization is parallel to the y axis, i.e. the external magnetic field is applied in that direction. Otherwise, two waves are coupled via \mathbf{h} .

Next, we examine the effect of the magnetoelastic coupling in the dynamics of the magnetostatic and elastic waves. In the absence of the coupling, the dynamics of magnetization \mathbf{m} upto its first-order is described by the linearized Landau-Lifshitz equation

$$\dot{\mathbf{m}} = -\gamma (\mathbf{m} \times \mathbf{H}_0 + \mathbf{M}_0 \times \mathbf{h}), \quad (13)$$

where γ is the gyromagnetic ratio. This equation can be derived from a Lagrangian

$$L^m[\mathbf{m}, \dot{\mathbf{m}}, \mathbf{m}^*, \dot{\mathbf{m}}^*] = \int dz \Re \left[\frac{\mu_0}{4M_0^2 \gamma} \mathbf{M}_0 \cdot (\mathbf{m} \times \dot{\mathbf{m}}^*) - \frac{\mu_0}{4} \left(\mathbf{h}^* \cdot \mathbf{h} + \frac{H_0}{M_0} \mathbf{m}^* \cdot \mathbf{m} \right) \right]. \quad (14)$$

We can check it by constructing the Euler-Lagrange equation with respect to \mathbf{m}^* from this Lagrangian. Here, μ_0 is the vacuum magnetic permeability, which

is required to make it consistent with the energy of the magnetic field. On the other hand, the dynamics of the displacement field \mathbf{u} is described by the Navier–Cauchy equation

$$\rho \ddot{\mathbf{u}} = \mu \nabla^2 \mathbf{u} + (\mu + \lambda) \nabla (\nabla \cdot \mathbf{u}), \quad (15)$$

where ρ is the mass density, μ and λ are Lamé constants. The Lagrangian for this equation is

$$L^u[\mathbf{u}, \dot{\mathbf{u}}, \mathbf{u}^*, \dot{\mathbf{u}}^*] = \int dz \left[\frac{\rho}{4} \dot{\mathbf{u}}^* \cdot \dot{\mathbf{u}} + \frac{1}{4} \partial_i \sigma_{ij} u_j^* \right], \quad (16)$$

where $\sigma_{ij} = \mu(\partial_i u_j + \partial_j u_i) + \lambda \delta_{ij} \nabla \cdot \mathbf{u}$ is the stress tensor. The total Lagrangian of a coupled system is given by the sum of two Lagrangians (14) and (16). In this case, \mathbf{h} is no longer just a functional of the amagnetization, but also a functional of the displacement field \mathbf{u} . Therefore, there appear a new volume force term $-\mu_0 \mathbf{f}$ in the Navier–Cauchy equation (15), where the force \mathbf{f} is given as (see Supplemental Material [1] for the detail of derivation)

$$f_i(z) := \frac{\delta h_j^*}{\delta u_i^*} h_j = -(\mathbf{M}_0 \cdot \nabla) h_i(z). \quad (17)$$

Physically, this force can be understood as a Maxwell stress acting on magnetic dipoles at each lattice site caused by the change of the dipolar field, which is induced by the displacement field. The coupled dynamics of the magnetoelastic wave is then given by

$$\begin{cases} \dot{\mathbf{m}} = -\gamma (\mathbf{m} \times \mathbf{H}_0 + \mathbf{M}_0 \times \mathbf{h}) \\ \rho \ddot{\mathbf{u}} = \mu \nabla^2 \mathbf{u} + (\mu + \lambda) \nabla (\nabla \cdot \mathbf{u}) - \mu_0 \mathbf{f}. \end{cases} \quad (18)$$

Acknowledgments

H. Y. Acknowledges support from Japan Society for the Promotion of Science (JSPS) KAKENHI Grant No. JP24KJ1109 and by MEXT Initiative to Establish Next-generation Novel Integrated Circuits Centers (X-NICS) Grant No. JPJ011438. S. M. acknowledges support by Japan Society for the Promotion of Science (JSPS) KAKENHI Grant No. JP22K18687, No. JP22H00108, and No. JP24H02231.

- [1] See Supplemental Material at url for details of derivations.
- [2] Kalinikos B A and Slavin A N 1986 *J. Phys. C: Solid State Phys.* **19** 7013