

FilaPro PETG - Technical Data Sheet

PETG offers good strength, chemical resistance and moderate heat resistance. Suitable for functional parts, containers and outdoor use. More prone to stringing than PLA.

Material Properties

Property	Value	Test method
Density	1.27 g/cm3	ISO 1183
Tensile strength	50 MPa	ISO 527
Elongation at break	23%	ISO 527
Heat deflection temp	70 C	ISO 75
Melt flow index	15 g/10min	240 C, 2.16 kg

Recommended Print Settings

Setting	Recommended	Range
Nozzle temperature	240 C	230-250 C
Bed temperature	80 C	70-85 C
Print speed	80 mm/s	40-150 mm/s
Cooling fan	40%	30-60%
Retraction (direct)	1.0 mm	0.8-2.0 mm

Storage and Drying

PETG absorbs moisture. Dry at 65 C for 6 hours before printing if the spool was open for more than a week.

Tips

- Do not print PETG directly on bare textured PEI with too low a Z-offset: it can bond too strongly. Use a release agent.
- Lower fan speed improves layer adhesion.
- Raise Z-offset by 0.02-0.04 mm compared to PLA.