

FilaPro PLA+ - Technical Data Sheet

PLA+ is a toughened polylactic acid. Easy to print, low warping, ideal for prototypes, decor and figurines. Not suitable for parts exposed to heat above 55 C.

Material Properties

Property	Value	Test method
Density	1.24 g/cm3	ISO 1183
Tensile strength	53 MPa	ISO 527
Elongation at break	12%	ISO 527
Heat deflection temp	56 C	ISO 75
Melt flow index	7 g/10min	210 C, 2.16 kg

Recommended Print Settings

Setting	Recommended	Range
Nozzle temperature	210 C	200-225 C
Bed temperature	60 C	50-65 C
Print speed	100 mm/s	40-200 mm/s
Cooling fan	100%	80-100%
Retraction (direct)	0.8 mm	0.5-1.5 mm

Storage and Drying

Store in a sealed bag with desiccant. If prints become brittle or stringy, dry at 50 C for 4 hours.

Tips

- Use a glue stick on smooth PEI if large flat parts lift.
- Avoid leaving prints in hot cars.
- Matte finishes print best at lower speeds.