

FilaPro TPU 95A - Technical Data Sheet

TPU 95A is a flexible thermoplastic polyurethane. Used for phone cases, gaskets, bumpers and wearable parts. Requires slow printing and a direct drive extruder.

Material Properties

Property	Value	Test method
Shore hardness	95A	ISO 868
Density	1.21 g/cm3	ISO 1183
Tensile strength	32 MPa	ISO 527
Elongation at break	550%	ISO 527
Heat deflection temp	60 C	ISO 75

Recommended Print Settings

Setting	Recommended	Range
Nozzle temperature	225 C	210-235 C
Bed temperature	50 C	40-60 C
Print speed	30 mm/s	15-40 mm/s
Cooling fan	60%	50-100%
Retraction (direct)	0.5 mm	0-1.0 mm

Storage and Drying

TPU is highly hygroscopic. Dry at 55 C for 8 hours. Print from a dry box when possible.

Tips

- Disable or minimise retraction to avoid jams.
- Bowden extruders are not recommended.
- Reduce max volumetric speed to 3 mm³/s.