

ERASTEEL TECHNICAL DATASHEET: ASP 2060

Application Family: Cutting tools | Standards: AISI M60 PM, W.-Nr. 1.3241

1. Grade Overview & Characteristics

ASP 2060 is one of the highest-alloyed powder metallurgy tool steels available, packing 10.5% cobalt and 6.5% vanadium. Delivers unbeatable hot hardness and abrasive wear resistance.

2. Nominal Chemical Composition (wt. % range)

Element	Carbon (C)	Chromium (Cr)	Molybdenum (Mo)	Tungsten (W)	Vanadium (V)	Cobalt (Co)	Other
Range %	2.25 - 2.35	4.0 - 4.4	6.8 - 7.2	6.3 - 6.7	6.3 - 6.7	10.2 - 10.8	Ultra-high carbon and vanadium

3. Mechanical Hardness & Property Profiles (Tempered state)

Metric	Value	Metric	Value (Rating 1-10)
Working Hardness Range	67.0 - 69.0 HRC	Machinability	4.0/10
Max Reachable Hardness	69.0 HRC	Wear Resistance	9.5/10
Annealed Delivery State	Max 280-350 HB	Toughness	5.0/10
Hot Hardness Retention	Secondary hardening	Hot Hardness	9.5/10
Heat Treatment Type	Vacuum / Salt bath	Grindability	4.5/10

4. Industrial Applications

High-speed dry gear hobbing, shaper cutters, broaches for nickel superalloys, cold forming tools under severe abrasive conditions.

5. Heat Treatment & Tempering Guidelines

Austenitizing at 1180-1210°C. Triple tempering at 560°C for 1 hour. Maximum working hardness 69 HRC.