Several investigations have documented that dislocations in silicon give rise to characteristic photoluminescence (PL) spectra below the band edge. First showed in [3] which labeled them D1 (0.812eV), D2 (0.875eV), D3 (0.934eV) and D4 (1.000eV). The samples where deformed at 850° C by bending, so that dislocation densities was inhomogeneous along the samples. [3] states that the intensity of theese lines increase when the dislocation-rich parts of the crystal is approached. At the same time the intensity of the intrinsic characteristics decrease. The distance between D1-D4 (62 ± 3 meV) corresponds to the energy of the optical phonons in silicon [3]. [3] reports D1 and D2 are dominant in heavily deformed Si crystals, while D3 and D4 predominate in weakly deformed Si. A similar result was also reported by [8] for small angle grain boundaries using cathodoluminescence.

[9] suggest that D1-D4 are due to dislocations which have been frozen in under low-shear stress. Photoluminescence under uniaxial stress shows that D1/D2 originate in the tetragonal defect with random orientation relative to <100> directions. [9] conclude that D3 and D4 are closely related, whereas the independent D1/D2 centers might be deformation-produced point defects in the strain region of dislocations. New lines D5 and D6 emerge when high-temperature, low-stress deformation is followed by low-temperature, high-stress deformation. [9] propose that line D5 is due to straight dislocations and D6 is due to stacking faults. [9] also suggest that D3/D4 photoluminescence is much more characteristic of the dislocations themselves than the D1/D2 emission lines.

The origin of D1 and D2 is not clear. It has been argued that they originate in electronic transition at the geometrical kinks on dislocations [12], point defects [9] and impurities [5] and/or from the reaction products of dislocations [10]. On the other hand, D3 and D4 lines is generally thought to be related to electronic transition within dislocation cores [7]. In addition, it has been suggested that the D3 line most likely is a phonon-assisted replica of D4 [7].

Both [3] and [9] studied plastically deformed silicon made by the Czochralski process (Cz-Si). [16] studied dislocations in multicrystalline silicon (mc-Si) and found similar lines with the entire set of D-lines shifted with around 10meV, presumably due to a strain field. Using a laser annealing technique [11] to introduce dislocations on a Cz-Si wafer, confirm the band location of D1-D4 from [9] in [16]. A principal difference between dislocation D'-lines in mc-Si versus D-lines in Cz-Si is a substantial broadening (60-70meV at 77K) of the D1'/D2' lines [16].

Cz-Si [3]	D1 0.812eV	D2 0.875eV	D3 0.934eV	D4 1.000eV
mc-Si [16]	D1' 0.80eV	D2' 0.89eV	D3' 0.95eV	D4' 1.00eV

Table 1: Energy positions of dislocation D-lines in Cz-Si and D' bands in mc-Si

[16] reveal a linear dependence of the band-to-band photoluminescence intensity and minority carrier lifetime across entire multicrystalline-Si wafers. Photoluminescence mapping in [16] of the 0.78eV (0.8eV) band intensity reveal a linkage to areas of a high dislocation density. This band should also be visible in room temperature [16].

[17] later found that if the contamination level is too low, or too high (dislocation decorated by metal silicate precipitates) the defect photoluminescence band vanished in room temperature. However, a relatively low contamination level of dislocations, in the order of 10 impurity atoms per micron of the dislocation length produces distinguishable defect band luminescence [17].

Dislocation related lines (D-lines) has been observed in low temperature photoluminiscence spectra from the regions which included the intragrain defects [14]. They also conclude that grain boundaries are not active recombination centers. [14] also show a TO-phonon replica of the boron bound exiton at 1.093eV. Intensity of boron bound exiton from the long lifetime regions was higher than that from the short lifetime regions. D-lines reported by [9] are in a short lifetime region. For a long lifetime region, [14] observe a peak at 1.00eV which is not the D4 line, but the zonecenter optical phonon sideband of the two-hole transition in the boron bound exiton [2]. There have been no reports on the D-line spectrum missing only the D1 line [14].

[13] study origins of the defects by low temperature photoluminescence spectroscopy, electron backscatter diffraction pattern measurement and the etch-pit observation, and conclude that defects are metal contaminated dislocation clusters which originated from small angle grain boundaries.

0.1 Impurities

Investigation in [4] show that transition-metal contamination plays an important role in the production of D-band luminescence from silicon samples containing either epitaxial stacking faults or oxidation-induced stacking faults. However, [10] later concluded that metallic impurities don't seem to be related to D1 and D2 luminescence.

Room temperature mapping of the 0.77eV band is attributed to oxygen precipitates in in thermally treated silicon made by the Czochralski process (Cz-Si) [15]. This band peak shifts parallel to the bandgap with temperature. The increase of this band on the dislocation lines is due to the preferential precipitation of oxygen [15].

[6] state that the deep-level emission from multicrystalline silicon with an intensity maximum at 0.78eV at room temperature is diffrent from that of the D1 line at low temperature. Furthermore, [6] suggest that the 0.78eV emission is associated with oxygen precipitation, and that the intra-grain defects are dislocation clusters decorated with oxygen impurities in addition to heavy-metal impurities.

Abbrevation	Description
B_{TO}	TO phonon replica of the Boron bound exiton [13]
D_a	Broad background emission [15]
D_b	Oxygen impurity band [15]
CZ-Si	Czochralski processed Silicon
D1	Dislocation related line 1 [3]
D1'	Dislocation related line 1 for mc-Si [16]
D2	Dislocation related line 2 [3]
D2'	Dislocation related line 2 for mc-Si [16]
D3	Dislocation related line 3 [3]
D3'	Dislocation related line 3 for mc-Si [16]
D4	Dislocation related line 4 [3]
D4'	Dislocation related line 4 for mc-Si [16]
EBIC	Electron beam induced current [1]
EBSP	Electron Backscatter Diffraction Pattern [13]
FZ-Si	Float-zone silicon
EFG	Edge-define Film-fed Growth
mc-Si	Multicrystalline silicon
R1BB	One phonon replica of band edge emission [1]
R2BB	Two phonon replica of band edge emission [1]
SA GB	Small Angle Grain Boundary

Table 2: Abbreviations

D1 and D2: It has been argued that they originate in electronic transition at the geometrical kinks on dislocations [12], point defects [9] and impurities [5] and/or from the reaction products of dislocations [10].

D3 and D4 lines is generally thought to be related to electronic transition within dislocation cores [7]. In addition, it has been suggested that the D3 line most likely is a phonon-assisted replica of D4 [7].

References

[1] Tz. Arguirov, W. Seifert, M. Kittler, and J. Reif. Temperature behaviour of extended defects in solar grade silicon investigated by photoluminescence and ebic. *Elsevier B.V.*, 2003.

[2] P. J. Dean, J.R. Haynes, and W.F. Flood. New radiative recombination processes involving neutral donors and acceptors in silicon and germanium. *Physical Review Volume 161 Number 3*, 1967.

[3] N. A. Drozdov, A.A. Patrin, and V.D Tkachev. Recombination radiation on dislocations in silicon. *Pis'ma Xh. Eksp. Teor. Fiz.*, 1976.

[4] V. Higgs, M. Goulding, and P. Kightley. Characterization of epitaxial and oxidation-induced stacking faults in silicon: The influence of transition-metal contamination. *Appl. Phys. Lett.*, 1992.

[5] V. Higgs, P. Kightley, P.J. Goodhew, and P.D. Augustus. Metal-induced dislocation nucleation for metastable sige/si. *Appl. Phys. Lett.*, 1991.

[6] M. Inoue, H. Sugimoto, M. Tajima, Y. Ohshita, and A. Ogura. Microscopic and spectroscopic mapping of dislocation-related photoluminescence in multicrystalline silicon wafers. *J. Mater Sci*, 2007.

[7] V.V Kveder, E.A. Steinman, S.A. Shevchenko, and H.G. Grimmeiss. Dislocation-related electroluminescence at room temperature in plastically deformed silicon. *Phys. Rev. B*, 1995.

[8] Woong Lee, Jun Chen, Bin Chen, Jiho Chang, and Takashi Sekiguchi. Cathodoluminescence study of dislocation-related luminescence from small-angle grain boundaries in multicrystalline silicon. *Applied Physics Letters*, 2009.

[9] R. Sauer, J. Weber, and J. Stolz. Dislocation-related photoluminescence in silicon. *Appl. Phys.*, 1985.

[10] T. Sekiguchi and K. Sumino. Cathodoluminescence study on dislocations in silicon. *J. Appl. Phys.*, 1995.

[11] W. Staiger, G. Pfeiffer, K. Weronek, A. Höpner, and J. Weber. Dislocation-induced defect levels in silicon. *Materials Science Forum*, 1994.

[12] M. Suezawa, Y. Sasaki, and K. Sumino. Dependence of photoluminescence on temperature in dislocated silicon crystals. *Physica Status Solidi*, 1983.

[13] H. Sugimoto, K. Araki, M. Tajima, T. Eguchi, I. Yamaga, M. Dhamrin, K. Kamisako, and T. Saitoh. Photoluminescence analysis of intragrain defects in multicrystalline silicon wafers for solar cells. *Journal of Applied Physics*, 2007.

[14] Hiroki Sugimoto, Masaaki Inoue, Michio Tajima, Atsushi Ogura, and Yoshio Ohsita. Analysis of intra-grain defects in multicrystalline silicon wafers by photoluminescence mapping and spectroscopy. *Japanese Journal of Applied Physics*, 2006.

[15] M. Tajima, M. Tokita, and M. Warashina. Photoluminescence due to oxygen precipitates distinguished from the d-lines in annealed si. *Materials Science Forum*, 1995.

[16] I. Tarasov, S. Ostapenko, C.Haessler, and E.-U. Reisner. Spatially resolved defect diagnostics in multicrystalline silicon for solar cells. *Elsevier Science S.A*, 2000.

[17] I. Tarasov, S. Ostapenko, W. Seifert, M. Kittler, and J.P. Kaleis. Defect diagnostics in multicrystalline silicon using scanning techniques. *Elsevier Science B.V.*, 2001.

A Silicon energy bands

Energy	**Name**	**Temp.**	**Impurity / Defect**	**Observed in**
0.76-0.8eV	Defect	290K	Dislocation with low contamination	[16] [17]
0.77-0.78eV	D_b	4.2-295K	Oxygen impurity band	[15] [6]
0.80eV	D1’	77K	Dislocations	[16] [17]
0.812eV	D1	4.2K	Dislocation related line	[3] [9] [1]
0.875eV	D2	4.2K	Dislocation related line	[3] [9] [1]
0.89eV	D2’	77K	Dislocations	[16] [17]
0.8-0.9eV	D_{a1}	11K	Broad background emission under D1/D2	[15]
0.934eV	D3	4.2K	Dislocations	[3] [9] [1]
0.95eV	D3’	77K	Dislocations	[16] [17]
0.953eV	D5	4.2K	Straight dislocations	[9]
0.98eV	R2BB	80K	Two phonon replica of band edge emission	[1]
0.9-1.0eV	D_{a2}	11K	Broad background emission under D3/D4	[15]
1.000eV	D4	4.2K	Dislocations	[3] [9] [1]
1.00eV	D4’	77K	Dislocations	[16] [17]
1.0126eV	D6	Stacking faults	[9]	
1.04eV	R1BB	80K	One phonon replica of band edge emission	[1]
1.092eV	BE1	4.2K	Bound exciton	[3]
1.093eV	B_{TO}	4.2K	TO phonon replica of Boron bound exiton	[13] **??**

Table 3: Silicon energy bands

Ref.	Sample type	Excitation process	Area	Processing	Doping
[13]	mc-Si	532nm $Nd:YVO_4$	$0.1mW/10\ \mu$m diameter	Sawing damage etched by HNO_3/HF	B-doped
[15]	Cz-Si	Kr ion laser 647nm	10 µm		Undoped
[3]	Cz-Si	Xenon lamp	50mW on 3mm modulated at 9Hz	deformed by bending at 850° C	undoped, weak n and p
[16]	mc-Si	800nm AlGaAs laser	Pulsed 300mW / 3mm	surface	Produced by block-casting technique for Baysix
[17]	mc-Si	800nm AlGaAs at 140mW		Produced by EFG	
[1]	mc-Si and FZ-Si	Ar ion 514nm at 300mW	100µm	Produced by EFG	boron doped 10^15cm^-1
[9]	FZ-Si	Kr-ion 647nm, Ar-ion 415nm and Nd-YAG 1064nm		Deformed a 650° C and 850° C	residual 10^{12}cm^{-3} boron
[6]	mc-Si	Nd:YVO 532nm	6mW, 10μm diameter	Slicing damage etched off by HNO_3/HF	boron doped

Table 4: Sample types