

TEST REPORT

Lucideon Reference: N26458 (QT-78966/4/KNA)/Ref. 7

Project Title: Determination of Water Vapour Transmission Properties - Cup Method in Accordance with BS EN ISO 12572:2016+A1:2014 of N10 Carbon Negative Bricks

Client: Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

For the Attention of: Ms Anna Simmons

Author(s): Miss Lisa Cobden

Report Date: 05 June, 2026

Purchase Order No.: PO-0003



Miss Joanne Booth
**Testing Team
Reviewer**



Miss Lisa Cobden
**Testing Team
Project Manager**



CONTENTS

	Page
1 INTRODUCTION	3
2 SAMPLES RECEIVED	3
3 TEST METHOD	3
4 RESULTS	4

1 INTRODUCTION

Earth4Earth Technology Ltd submitted samples of their N10 Carbon Negative bricks for Determination of water vapour transmission properties – Cup method in accordance with BS EN ISO 12572:2016+A1:2014.

The testing was performed at the Lucideon Structures Laboratory at Queens Road, Penkhull, Stoke-on-Trent, Staffordshire, ST4 7LQ, UK concluding in May 2026

2 SAMPLES RECEIVED

Solid bricks referenced as N10 Carbon Negative were received from the client.

The bricks were nominally 215 mm x 102.5 mm x 65 mm (length x width x height).

The bricks were solid with a nominal compressive strength of 39.1 N/mm².

3 TEST METHOD

The determination of water vapour resistance was carried out according to BS EN 12572:2016+A1:2014.

100 mm diameter cores were sampled from the bricks.

The samples were stored at 23°C, 50% relative humidity until a constant mass was achieved.

Conditions were set such that the temperature was at 23°C with the relative humidity being 93% inside the dish (wet state) and the relative humidity being 50% outside the dish and sample (dry state).

An aqueous solution of ammonium dihydrogen phosphate was used to obtain 93% relative humidity.

The test samples were sealed into a glass cup using a wax system with an air gap of 15 mm maintained between the 15 mm of aqueous solution and the test sample, with the sides of the samples protruding above the glass cup using the same wax system.

The samples were stored in an environmental chamber controlled at 23 (± 2)°C, and 50 (± 5)% relative humidity and weighed to 3 No. decimal places at specific time intervals, until 5 No. successive determinations of change in mass per weighing interval for each test sample were obtained.

The mass change rate was calculated and used to calculate the water vapour resistance.

4 RESULTS

Table 1 – Calculation of Difference in Vapour Pressure

	Humidity RH (%)	Temperature (°C)	Vapour Pressure (Pa)	The Value of Δp
Inside	0.93	23	2611.3	1207
Ambient	0.50	23	1403.9	

Table 2 – Results for the Determination of Earth4Earth Technology N10 Carbon Negative Bricks Water Vapour Transmission Properties

Sample No.	Gradient (mg/h)	Area (m ²)	Density of Water Vapour Flow Rate (mg/(m ² h))	Water Vapour Permanence (mg/Pa.m ² h)	Water Vapour Resistance (Pa.m ² .h/mg)	Water Vapour Permeability (mg/m.h.Pa)
1	6.067	0.0079	772.488	0.640	1.562	0.042
2	6.486	0.0079	825.876	0.684	1.461	0.044
3	7.026	0.0079	894.622	0.741	1.349	0.048
4	8.304	0.0079	1057.263	0.876	1.142	0.057
5	7.226	0.0079	920.006	0.762	1.312	0.050
Mean	7.022	0.0079	894.05	0.741	1.365	0.048

To obtain an equivalent air layer thickness (s_d), first the values for δ_p , δ_a and the μ value must be found. Using the mean water vapour permeance (W) and sample thickness (d), δ_p can be calculated with the following equation, given in Part 8.5 of the Standard:

$$\delta_p = W \cdot d$$

Where δ_p was calculated to be 0.009 mg/m²h*Pa.

δ_a can be calculated with the following equation, given in Part 8.6 of the Standard:

$$\delta_a = ((0.086 \cdot p_0) / (R_v \cdot T \cdot p)) \cdot (T/273)^{1.81}$$

Where p_0 is 1013.25 h.Pa as given in Part 3.2 of the Standard, R_v is 0.000462 N*m/mg.K as given in Part 8.6, T is the temperature of the lab in Kelvin and p is found according to Formula 4 in the Standard. This gives δ_a to be 0.714 mg/m²h*Pa.

The μ value can be found using the following equation, given in Part 8.6 of the Standard:

$$\mu = (\Delta p_v \cdot \delta_a) / (g \cdot d)$$

Where Δp_v is 1207 Pa as given in Table 2 in the Standard. This gives an average μ value of 15.006

Equivalent air layer thickness (s_d) can now be calculated using the equation, given in Part 8.7 of the Standard:

$$S_d = \mu \cdot d$$

Therefore, for the samples of the Earth4Earth Technology N10 Carbon Negative bricks, the values for each of the calculated properties are as follows:

Table 3 – Calculated Properties

Property	Symbol	Value as Calculated
Density of water vapour flow rate	g	894.05 (mg.h.m ²)
Water vapour permeance	W _p	0.741mg/(m ² .h.Pa)
Water vapour resistance	Z	1.365 (m ² .h.Pa/mg)
Water vapour permeability	δ _p	0.048 (mg/m.h.Pa)
Water vapour resistance factor	μ	15.006
Water vapour diffusion equivalent air layer thickness	S _d	1.00 (m)

NOTE: The results given in this report apply only to the samples that have been tested.

END OF REPORT