

STRUCTURES ANALYSIS REPORT



0013

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Anna Simmons

Report of Tests on: Cabon Capture Brick L10

Your Reference: 20250002

Lucideon Reference: N26730 - 2

Date Reported: 08-May-2026

Order Number: Proforma Invoice PO-0004

Date Logged: 20-Feb-2026

Date(s) of Test(s): 10-Mar-2026 to 10-Mar-2026

Determination of Dimensions, Flatness and Plane Parallelism

BSEN 771-3: 2011 (BSEN 772-16: 2011, BSEN772-20: 2000)

	Length	Width	Height	Flatness	Parallelism
No.	mm	mm	mm	mm	mm
1	215.0	102.5	65.0	0.1	0.5
2	215.0	102.5	64.5	0.1	0.2
3	215.0	102.5	66.0	0.1	0.6
4	215.0	102.5	65.5	0.1	0.3
5	215.0	103.0	65.0	0.1	0.9
6	215.0	102.5	66.0	0.1	1.1
Mean	215.0	103.0	65.0	0.1	0.6

Sample Preparation Procedure: OP148

Name of organisation carrying out sampling: Earth4Earth

Method of Sampling: Not Supplied

Method of Measurement: Method B

Measuring Device: Digital Calipers

Precision of Measuring Device: 2 decimal places

The sample was deviating and as a result, the test result(s) may be invalid.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

K. Zar

Mr Kaleem Zar

Reviewer

B. Mann

Mr Bevan Mann

Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

Lucideon Limited T +44 (0)1785 331874
Queens Road, Penkhull query@lucideon.com
Stoke-on-Trent www.lucideon.com
Staffordshire, ST4 7LQ, UK Reg. England 1960455

STRUCTURES ANALYSIS REPORT

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Anna Simmons

Report of Tests on: Cabon Capture Brick L10

Your Reference: 20250002

Lucideon Reference: N26730 - 2

Date Reported: 08-May-2026

Order Number:

Proforma Invoice PO-0004

Date Logged: 20-Feb-2026

Date(s) of Test(s):

10-Mar-2026 to 10-Mar-2026

Determination of Initial Rate of Water Absorption

BS EN 772-11: 2011 (Clay masonry units)

No.	Initial Rate of Water Absorption kg/(m ² .min)
1	1.0
2	0.5
3	0.4
4	0.5
5	0.7
6	0.6
7	0.4
8	0.4
9	0.4
10	0.4
Mean	0.5

Sample Preparation Procedure: OP148

Name of organisation carrying out sampling: Earth4Earth

Method of Sampling: Not Supplied

The sample was deviating and as a result, the test result(s) may be invalid.

End of Test Report

K. Zar

Mr Kaleem Zar

Reviewer

B. Mann

Mr Bevan Mann

Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

STRUCTURES ANALYSIS REPORT



0013

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Anna Simmons

Report of Tests on: Cabon Capture Brick L10

Your Reference: 20250002

Lucideon Reference: N26730 - 2

Date Reported: 08-May-2026

Order Number:

Proforma Invoice PO-0004

Date Logged: 20-Feb-2026

Date(s) of Test(s):

19-Mar-2026 to 19-Mar-2026

Determination of Compressive Strength
BS EN 772-1: 2011 (By Surface Grinding) + A1 2015

	Brick Length	Brick Width	Load	Compressive Strength
No.	mm	mm	kN	N/mm ²
1	214.9	102.7	1007	45.6
2	215.2	102.5	1064	48.2
3	215.1	102.6	1178	53.4
4	215.1	102.6	1111	50.3
5	215.1	102.8	1118	50.6
6	214.4	102.4	1158	52.7
7	215.0	102.7	1153	52.2
8	215.2	102.9	1158	52.3
9	215.0	102.7	1171	53.0
10	215.0	102.5	1108	50.3
Mean	215.0	103.0	1122.6	50.9

Sample Preparation Procedure: OP148

Name of organisation carrying out sampling: Earth4Earth

Method of Sampling: Not Supplied

Method of Conditioning: Dryer at 105 deg C

Method of Preparation: Surface Ground

Orientation of Loading: Bed Face

Coefficient of Variation: 4.8 %

Crushing Machine: 3000KN

Machine Number: 90011

Serial Number: COM018

The sample was deviating and as a result, the test result(s) may be invalid.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

K. Zar

Mr Kaleem Zar

Reviewer

B. Mann

Mr Bevan Mann

Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

STRUCTURES ANALYSIS REPORT



0013

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Anna Simmons

Report of Tests on: Cabon Capture Brick L10

Your Reference: 20250002

Lucideon Reference: N26730 - 2

Date Reported: 08-May-2026

Order Number:

Proforma Invoice PO-0004

Date Logged: 20-Feb-2026

Date(s) of Test(s):

13-Apr-2026 to 08-May-2026

Determination of Moisture Movement

BS EN 772-14: 2002

	Dry Weight (Moisture Expansion)	Moisture Expansion	Dry Weight (Drying Shrinkage)	Drying Shrinkage	Moisture Content
No.	kg	mm/m	kg	mm/m	%
1	-	-	2.8	0.87	2.8
2	2.9	1.26	-	-	-
3	-	-	2.9	0.86	2.8
4	2.9	1.18	-	-	-
5	-	-	2.9	0.82	2.5
6	3.0	0.90	-	-	-
Mean	-	1.11	-	0.85	3

Sample Preparation Procedure: OP148

Block 1 = 1

Block 2 = 2

Block 3 = 3

Block 4 = 4

Block 5 = 5

Block 6 = 6

Total Movement: 1.96 mm/m

Name of organisation carrying out sampling: Earth4Earth

Method of Sampling: Not Supplied

Storage Condition: As Clause 6.2 of the above Standard with the exception of the blocks not being in plastic

Blocks 2,4,6 used for moisture expansion, blocks 1,3,5 used for drying shrinkage and moisture content.

The sample was deviating and as a result, the test result(s) may be invalid.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

K. Zar

Mr Kaleem Zar

Reviewer

B. Mann

Mr Bevan Mann

Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.

STRUCTURES ANALYSIS REPORT



0013

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Anna Simmons

Report of Tests on: Cabon Capture Brick L10

Your Reference: 20250002

Lucideon Reference: N26730 - 2

Date Reported: 08-May-2026

Order Number: Proforma Invoice PO-0004

Date Logged: 20-Feb-2026

Date(s) of Test(s): 16-Mar-2026 to 17-Mar-2026

Determination of Net & Gross Dry Density of Masonry Units (Except for Natural Stone)

BS EN 772-13:2000

	Net Dry Density	Gross Dry Density
No.	kg/m ³	kg/m ³
1	1890	1890
2	1930	1930
3	2020	2020
4	1980	1970
5	1970	1950
6	1960	1960
7	1970	1970
8	2000	2000
9	2010	2010
10	1970	1970
Mean	1970	1970

Sample Preparation Procedure: OP148

Name of organisation carrying out sampling: Earth4Earth

Method of Sampling: Not Supplied

The sample was deviating and as a result, the test result(s) may be invalid.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

K. Zar

Mr Kaleem Zar

Reviewer

B. Mann

Mr Bevan Mann

Author

Page 1 of 1

This report is issued in accordance with the Conditions of Business of Lucideon Limited and relates only to the sample(s) tested. No responsibility is taken for the accuracy of the sampling unless this is done under our own supervision. This report shall not be reproduced in part without the written approval of Lucideon Limited, nor used in any way as to lead to misrepresentation of the results or their implications.

Lucideon is the trading name of Lucideon Limited. Registered in England No. 1960455.