

PHYSICAL TESTING REPORT



0013

Earth4Earth Technology Ltd
85 Great Portland Street
London
W1W 7LT

FAO: Ms. Yan Geng

Report of Tests on: Carbon Capture Brick N10

Your Reference: N10/14-1

Lucideon Reference: N253627 - 2

Date Reported: 30-Oct-2025

Order Number:

Proforma Invoice

Date Logged: 21-Aug-2025

Date(s) of Test(s):

03-Oct-2025 to 24-Oct-2025

Determination of Moisture Movement

BS EN 772-14: 2002

	Dry Weight (Moisture Expansion)	Moisture Expansion	Dry Weight (Drying Shrinkage)	Drying Shrinkage	Moisture Content
No.	kg	mm/m	kg	mm/m	%
1	-	-	2.7	0.35	1.3
2	2.8	1.18	-	-	-
3	-	-	2.8	0.38	1.6
4	2.8	1.34	-	-	-
5	-	-	2.9	0.34	1.6
6	2.9	1.21	-	-	-
Mean	-	1.24	-	0.36	2

Sample Preparation Procedure: OP148

Block 1 = 1

Block 2 = 2

Block 3 = 3

Block 4 = 4

Block 5 = 5

Block 6 = 6

Total Movement: 1.60 mm/m

Name of organisation carrying out sampling: EARTH 4 EARTH

Method of Sampling: Not Supplied

Storage Condition: As Clause 6.2 of the above Standard with the exception of the blocks not being in plastic bags.

Blocks 2,4,6 used for moisture expansion, blocks 1,3,5 used for drying shrinkage and moisture content.

The sample was deviating and as a result, the test result(s) may be invalid.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

End of Test Report

Mr Kaleem Zar
Engineer