

TEST REPORT

No. : SHIN2511002964CM05_EN

Date : 2025-12-17

Page: 1 of 4

CUSTOMER NAME: EARTH4EARTH TECHNOLOGY LTD

ADDRESS: 85 GREAT PORTLAND STREET LONDON ENGLAND W1W 7LT

Sample Name : L10 LOW CARBON BRICKS

Product Specification : 215*102.5*65 mm

Manufacturer : earth4Earth Technology(Wuhan) Co., Ltd.

Manufacturer Address : No.122, Xingguang Changwei Industrial Park, Caidian District, Wuhan
City, Hubei Province, China

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SHIN2511000529CPC06

Date of Receipt : 2025-11-06

Testing Period : 2025-11-06 ~ 2025-12-17

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd..

Xander Yang

Authorized signatory

TEST REPORT

No. : SHIN2511002964CM05_EN

Date : 2025-12-17

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Water Absorption (External Element)	EN 771-1:2011+A1:2015 Clause 5.3.7.1 & EN 772-21:2011	13 %	N/A
2	Water Absorption (Damp Proof Course Units)	EN 771-1:2011+A1:2015 Clause 5.3.7.2 & EN 772-7:1998	12.1 %	N/A

Note: Pass : Meet the requirements;
Fail : Does not meet the requirements;
N/A : Not Apply to the judgment.

Original Sample Photo:



TEST REPORT

No. : SHIN2511002964CM05_EN

Date : 2025-12-17

Page: 3 of 4

1. Test Item: Water Absorption (External Element)

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.7.1 & EN 772-21:2011

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 10pcs

Treatment condition: Dry at 105℃ to constant mass → Immersion in water for 24h

Test Result:

Test Item	Test Result					
	Individual Value					Average Value
Water Absorption (%)	13	12	12	13	13	13
	13	13	13	12	13	

TEST REPORT

No. : SHIN2511002964CM05_EN

Date : 2025-12-17

Page: 4 of 4

2. Test Item: Water Absorption (Damp Proof Course Units)

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.7.2 & EN 772-7:1998

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 10pcs

Treatment condition: Dry at 105℃ to constant mass → Boiling water for 5 hours → 23℃, 16h

Test Result:

Test Item	Test Result					
	Individual Value					Average Value
Water Absorption (%)	13.0	11.8	12.1	12.9	11.2	12.1
	12.7	12.0	11.9	12.0	11.7	

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

*****End of report*****