

TEST REPORT

No. : SHIN2511002964CM04_EN

Date : 2025-12-17

Page: 1 of 4

CUSTOMER NAME: EARTH4EARTH TECHNOLOGY LTD

ADDRESS: 85 GREAT PORTLAND STREET LONDON ENGLAND W1W 7LT

Sample Name : L10 LOW CARBON BRICKS

Product Specification : 215*102.5*65 mm

Manufacturer : earth4Earth Technology(Wuhan) Co., Ltd.

Manufacturer Address : No.122, Xingguang Changwei Industrial Park, Caidian District, Wuhan
City, Hubei Province, China

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SHIN2511000529CPC05

Date of Receipt : 2025-11-06

Testing Period : 2025-11-06 ~ 2025-12-17

Test result(s) : For further details, please refer to the following page(s)

(Unless otherwise stated the results shown in this test report refer only
to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd..

Xander Yang

Authorized signatory

TEST REPORT

No. : SHIN2511002964CM04_EN

Date : 2025-12-17

Page: 2 of 4

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Net Dry Density	EN 771-1:2011+A1:2015 Clause 5.3.3.2 & 5.3.3.3 & EN 772-13:2000 Clause 7.2	1920 kg/m ³	N/A
2	Gross Dry Density	EN 771-1:2011+A1:2015 Clause 5.3.3.1 & 5.3.3.3 & EN 772-13:2000 Clause 7.3	1930 kg/m ³	N/A

Note: Pass : Meet the requirements;
Fail : Does not meet the requirements;
N/A : Not Apply to the judgment.

Original Sample Photo:



TEST REPORT

No. : SHIN2511002964CM04_EN

Date : 2025-12-17

Page: 3 of 4

1. Test Item: Net Dry Density

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.3.2 & 5.3.3.3 & EN 772-13:2000 Clause 7.2

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 10pcs

Treatment condition: Dry at 105℃ to constant mass → Immersion in water to constant mass

Test Result:

Test Item	Test Result					
	Individual Value					Average Value
Net Dry Density (kg/m³)	1920	1960	1970	1900	1920	1920
	1920	1920	1930	1920	1890	

TEST REPORT

No. : SHIN2511002964CM04_EN

Date : 2025-12-17

Page: 4 of 4

2. Test Item: Gross Dry Density

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.3.1 & 5.3.3.3 & EN 772-13:2000 Clause 7.3

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 10pcs

Test Result:

Test Item	Test Result					
	Individual Value					Average Value
Gross Dry Density (kg/m ³)	1930	1950	1980	1900	1910	1930
	1940	1880	1940	1930	1930	

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

*****End of report*****