

TEST REPORT

No. : SHIN2511002964CM02_EN

Date : 2025-12-17

Page: 1 of 3

CUSTOMER NAME: EARTH4EARTH TECHNOLOGY LTD
ADDRESS: 85 GREAT PORTLAND STREET LONDON ENGLAND W1W 7LT

Sample Name : L10 LOW CARBON BRICKS
Product Specification : 215*102.5*65 mm
Manufacturer : earth4Earth Technology(Wuhan) Co., Ltd.
Manufacturer Address : No.122, Xingguang Changwei Industrial Park, Caidian District, Wuhan
City, Hubei Province, China

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SHIN2511000529CPC02
Date of Receipt : 2025-11-06
Testing Period : 2025-11-06 ~ 2025-12-17
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd..

Xander Yang
Authorized signatory

TEST REPORT

No. : SHIN2511002964CM02_EN

Date : 2025-12-17

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Flatness of Bed Faces	EN 771-1:2011+A1:2015 Clause 5.3.1.2.4 & EN 772-20:2000	0.2 mm	N/A
2	Plane Parallelism of Bed Faces	EN 771-1:2011+A1:2015 Clause 5.3.1.2.5 & EN 772-16:2011 Clause 7.4	0.8 mm	N/A

Note: Pass : Meet the requirements;
Fail : Does not meet the requirements;
N/A : Not Apply to the judgment.

Original Sample Photo:



TEST REPORT

No. : SHIN2511002964CM02_EN

Date : 2025-12-17

Page: 3 of 3

1. Test Item: Flatness of Bed Faces

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.1.2.4 & EN 772-20:2000

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 3pcs

Test Result:

Test Item	Test Result						
	Individual Value						Average Value
Flatness of Bed Faces (mm)	0.2	0.1	0.2	0.1	0.2	0.2	0.2

2. Test Item: Plane Parallelism of Bed Faces

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.1.2.5 & EN 772-16:2011 Clause 7.4

Test Condition:

Specimen: 215mm×102.5mm×65.0mm, 3pcs

Test Result:

Test Item	Test Result			
	Individual Value			The Largest Value
Plane Parallelism of Bed Faces (mm)	0.8	0.2	0.2	0.8

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

*****End of report*****