

TEST REPORT

No. : SHIN2511002964CM03_EN

Date : 2025-12-17

Page: 1 of 3

CUSTOMER NAME: EARTH4EARTH TECHNOLOGY LTD
ADDRESS: 85 GREAT PORTLAND STREET LONDON ENGLAND W1W 7LT

Sample Name : L10 LOW CARBON BRICKS
Product Specification : 215*102.5*65 mm
Manufacturer : earth4Earth Technology(Wuhan) Co., Ltd.
Manufacturer Address : No.122, Xingguang Changwei Industrial Park, Caidian District, Wuhan
City, Hubei Province, China

Above information and sample(s) was/were submitted and confirmed by the client. SGS, however, assumes no responsibility to verify the accuracy, adequacy and completeness of the sample information provided by client.

SGS Ref. No. : SHIN2511000529CPC03
Date of Receipt : 2025-11-06
Testing Period : 2025-11-06 ~ 2025-12-17
Test result(s) : For further details, please refer to the following page(s)
(Unless otherwise stated the results shown in this test report refer only to the sample(s) tested)

Signed for
SGS-CSTC Standards Technical
Services (Shanghai) Co., Ltd..

Xander Yang
Authorized signatory

TEST REPORT

No. : SHIN2511002964CM03_EN

Date : 2025-12-17

Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Compressive Strength	EN 771-1:2011+A1:2015 Clause 5.3.4 & EN 772-1:2011+A1:2015	35.8 N/mm ²	N/A

Note: Pass : Meet the requirements;
 Fail : Does not meet the requirements;
 N/A : Not Apply to the judgment.

Original Sample Photo:



TEST REPORT

No. : SHIN2511002964CM03_EN

Date : 2025-12-17

Page: 3 of 3

Test Item: Compressive Strength

Test Method: EN 771-1:2011+A1:2015 Clause 5.3.4 & EN 772-1:2011+A1:2015

Test Condition:

- Specimen: 215mm×102.5mm×65.0mm, 10pcs
- Treatment condition: 7.3.2b (105℃, 24h→23℃, 4h)
- Test rate: 0.3 (N/mm²)/s

Test Result:

Test Item	Test Result					
	Individual Value					Average Value
Compressive Strength (N/mm²)	35.5	34.7	35.0	36.3	40.0	35.8
	38.2	39.9	27.7	38.8	32.0	

The test report shall only be used for clients' scientific research, teaching, internal quality control, product research and development, etc... and just for internal reference.

*****End of report*****