



中国认可
国际互认
检测
TESTING
CNAS L0167

Test Report

No. CANHG2016553702

Date: 27 Sep 2020

Page 1 of 5

HUIZHOU ANBOSON TECHNOLOGY CO., LTD

2-3 / F, NO.7, HECHANG EAST 4TH ROAD, ZHONGKAI HIGH TECH ZONE, HUIZHOU CITY, GUANGDONG, CHINA

The following sample(s) was/were submitted and identified on behalf of the clients as : Disposable Nitrile Gloves

SGS Job No. : GZHL2009048522CW - GZ
Tested Sample Info. : Style / Item No.: ABC-NIT01
Supplier : HUIZHOU ANBOSON TECHNOLOGY CO., LTD
Country of Origin : CHINA
Country of Destination : EU
Date of Sample Received : 21 Sep 2020
Testing Period : 21 Sep 2020 - 27 Sep 2020
Test Requested : Selected test(s) as requested by client.
Test Method : Please refer to next page(s).
Test Results : Please refer to next page(s).

Signed for and on behalf of
SGS-CSTC Standards Technical Services Co., Ltd. Guangzhou Branch

Ivy Ren

Ivy Ren
Approved Signatory

scan to see the report



CANHG2016553702

This test report is the English version of CANHG2016553701. In case of any discrepancy, the Chinese version shall prevail.
本测试报告是CANHG2016553701的英文版本。中英文版本如有歧异，以中文版为准。



SGS-CSTC Standards Technical Services Co., Ltd.
Guangzhou Branch Testing Center Chemical Laboratory.

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

198 Kazhu Road, Sciotech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075113 www.sgs.com.cn
中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075113 e sgs.china@sgs.com



中国认可
国际互认
检测
TESTING
CNAS L0167

Test Report

No. CANHG2016553702

Date: 27 Sep 2020

Page 2 of 5

Result Summary :

Test Requested	Comments
GB 4806.11-2016-Sensory (Appearance: Normal color, no smell, no dirty)	PASS
GB 4806.11-2016-Sensory (Marinate: Colorless, no turbidity, no precipitate, no smell, or other sensory deterioration)	PASS
GB 4806.11-2016- Specific Migration of 1,3-Butadiene	PASS
GB 4806.11-2016- Residual 1, 3-Butadiene	PASS
GB 4806.11-2016- Specific Migration of acrylonitrile	PASS
GB 4806.11-2016 — Overall migration	PASS
GB 4806.11-2016 — Heavy metal (as Lead)	PASS
GB 4806.11-2016 — Consumption of Potassium Permanganate	PASS



SGS-CSTC Shenzhen Technical Services Co., Ltd.
Guangzhou Branch Testing Center Chemical Laboratory

Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

198 Kazhu Road, Sciotech Park Guangzhou Economic & Technology Development District, Guangzhou, China 510663 t (86-20) 82155555 f (86-20) 82075113 www.sgs.com.cn
中国·广州·经济技术开发区科学城科珠路198号 邮编: 510663 t (86-20) 82155555 f (86-20) 82075113 e sgs.china@sgs.com

Test Report

No. CANHG2016553702

Date: 27 Sep 2020

Page 3 of 5

Test Results :

Test Part Description :

Specimen No.	SGS Sample ID	Description	Material (claimed by the client)
SN1	CAN20-165537.001	Blue rubber gloves	Nitrile rubber

GB 4806.11-2016- Specific Migration of 1,3-Butadiene

Test Method : GB 31604.12-2016.

Simulant Used : 4% Acetic acid (V/V)

Test Condition : 40 °C 0.5 hr(s)

Test Item(s)	CAS NO.	Limit	Unit	RL	001
Migration times		-	-	-	1st
Area/Volume		-	dm ² /kg	-	6.0
1,3-butadiene	106-99-0	0.01	mg/kg	0.01	ND
Comment					PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
2. RL = Report Limit
3. ND= Not Detected(less than RL)

GB 4806.11-2016- Residual 1, 3-Butadiene

Test Method : GB 31604.12-2016.

Test Item(s)	CAS NO.	Limit	Unit	RL	001
1,3-butadiene	106-99-0	1	mg/kg	0.2	ND
Comment					PASS

Notes :

1. mg/kg = milligram per kilogram
2. RL = Report Limit
3. ND= Not Detected(less than RL)

GB 4806.11-2016- Specific Migration of acrylonitrile

Test Method : GB 31604.17-2016.

Simulant Used : 4% Acetic acid (V/V)



Test Report

No. CANHG2016553702

Date: 27 Sep 2020

Page 4 of 5

Test Condition : 40 °C 0.5 hr(s)

Test Item(s)	Limit	Unit	RL	001
Migration times	-	-	-	1st
Area/Volume	-	dm ² /kg	-	6.0
acrylonitrile	0.01	mg/kg	0.01	ND
Comment				PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
2. RL = Report Limit
3. ND= Not Detected(less than RL)

GB 4806.11-2016—Overall migration

Test Method : GB 31604.8-2016.

Simulant Used	Time	Temp	Limit	Unit	RL	001	Comment
10% Ethanol (V/V) Aqueous Solution	0.5 hr(s)	40 °C	10	mg/dm ²	3.0	4.7	PASS
4% Acetic Acid (V/V) Aqueous Solution	0.5 hr(s)	40 °C	10	mg/dm ²	3.0	7.4	PASS
50% Ethanol (V/V) Aqueous Solution	0.5 hr(s)	40 °C	10	mg/dm ²	3.0	7.9	PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
mg/dm² = milligram per square decimeter
2. RL = Report Limit
3. ND= Not Detected(less than RL)

GB 4806.11-2016—Heavy metal (as Lead)

Test Method : GB 31604.9-2016 Method 1.

Simulant Used	Time	Temp	Limit	Unit	RL	001	Comment
4% Acetic acid (V/V)	0.5 hr(s)	60 °C	1	mg/kg	-	<1	PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
2. RL = Report Limit
3. <=Less than



Test Report

No. CANHG2016553702

Date: 27 Sep 2020

Page 5 of 5

GB 4806.11-2016—Consumption of Potassium Permanganate

Test Method : GB 31604.2-2016.

<u>Simulant Used</u>	<u>Time</u>	<u>Temp</u>	<u>Limit</u>	<u>Unit</u>	<u>RL</u>	<u>001</u>	<u>Comment</u>
Distilled Water	0.5 hr(s)	60 °C	10	mg/kg	1.0	4.6	PASS

Notes :

1. mg/kg = milligram per kilogram of foodstuff in contact with
2. RL = Report Limit
3. ND= Not Detected(less than RL)

Sample photo:



SGS authenticate the photo on original report only

*** End of Report ***

