Refractive Index Sensors Based on the Long Period Grating Inscribed in Tapered Few Mode Fiber

Peng Wei

Key Laboratory of Specialty Fiber
Optics and Optical Access Networks,
Joint International Research
Laboratory of Specialty Fiber Optics
and Advanced Communication
Shanghai Institute for Advanced
Communication and Data Science,
Shanghai University
Shanghai, China
wp21@shu.edu.cn

Yungi Liu*

Key Laboratory of Specialty Fiber
Optics and Optical Access Networks,
Joint International Research
Laboratory of Specialty Fiber Optics
and Advanced Communication
Shanghai Institute for Advanced
Communication and Data Science,
Shanghai University
Shanghai, China
yqliu@shu.edu.cn

Long Chen

Key Laboratory of Specialty Fiber
Optics and Optical Access Networks,
Joint International Research
Laboratory of Specialty Fiber Optics
and Advanced Communication
Shanghai Institute for Advanced
Communication and Data Science,
Shanghai University
Shanghai, China
Clong@shu.edu.cn

Yuehui Ma

Key Laboratory of Specialty Fiber
Optics and Optical Access Networks,
Joint International Research
Laboratory of Specialty Fiber Optics
and Advanced Communication
Shanghai Institute for Advanced
Communication and Data Science,
Shanghai University
Shanghai, China
yhuima@shu.edu.cn

Abstract—We proposed a high sensitivity refractive index sensor based on tapered few mode fiber long-period fiber gratings. The sensitivity of the sensor can be up to 4632nm/RIU.

Keywords—Tapered, Long-period fiber grating

I. INTRODUCTION

With the maturity of optical fiber preparation technology, long-period fiber gratings are widely used in optical fiber communication and optical fiber sensing due to the advantages of low cost, flexible design and mature preparation process. Long-period fiber gratings are affected by various parameters such as refractive index[1], temperature[2], strain[3], etc., and are manifested as the offset of resonant peaks in the transmission spectrum, and the sensing of corresponding parameters can be realized by measuring the change of resonance wavelength, which has attracted more and more attention in the field of optical fiber sensing.

Fan et al. used the arc discharge method to prepare LPFG on a tapered fiber with a diameter of 6.3 μm , and the SRI sensitivity was up to 3762 nm/RIU[4]. Fu et al. used the optical fiber splicer to pull the FM-LPFG to prepare a high-sensitivity tapered FM-LPFG temperature sensor, when the temperature is in the range of 30 °C \sim 90 °C, the temperature sensitivity of the sensor can reach 0.0393nm/°C[5]. Liu et al. proposed a novel tapered two-mode fiber embedded long-period fiber grating (TTMF-LPFG) sensor, when the taper waist diameter is 36 μm , the maximum SRI sensitivity reaches 1360.43 nm/RIU[6].

In this work, We prepared long-period fiber gratings of tapered few-mode fiber. The influence of different taper waist diameters on the refractive index sensitivity was investigated. Such a high sensitivity refractive index sensor has a potential application in many fields.

II. THEORTICAL ANALYSIS AND FABRICATION

A. Theoretical Analysis

In the experiment, the fiber used is a step-index FMF(YOFC)[7]. The FMF has a core diameter of $16\mu m$, a cladding diameter of $125\mu m$, and the RI difference between the cladding and core of fiber is 0.01.

On the basic of the coupled mode theory, the phase matching condition of LPFG is given by[8]

$$\lambda_{res} = (n_{eff,co} - n_{eff,cl}) \Lambda \tag{1}$$

where, λ_{res} is the resonance wavelength, $n_{eff,co}$ and $n_{eff,cl}$ represent the effective RI of the core mode and cladding mode, respectively, Λ represents the LPFG period.

B. Fabrication

In the experiment, the preparation of long-period fiber gratings of tapered few mode fiber was divided into two steps, firstly, the carbon dioxide-laser glass-processing system(AFL Fujikura,LZM-100) was used as the heating source to prepare the tapered fiber, and then LPFGs was prepared on the fiber after tapered.




Fig. 1 Schematic diagram of the experimental setup

The LPFGs were fabricated by a CO₂ laser (CO₂-H10, Han's Laser) through point by point inscription in the FMF. The average power and the pulse frequency of the CO₂ laser were 0.6W and 5kHZ, respectively. The schematic diagram of the experimental setup for the LPFG fabrication is shown in Fig. 1. Both ends of FMF were spliced with single-mode fibers (SMFs). The focused laser beam scanned the fiber along the fiber axis. The laser scanned processes may be repeated for several cycles until a LPFG with high spectral contrast was formed. Light from a supercontinuum broadband light source (NKT Photonics) was launched into the FMF, and the transmission spectra of the gratings were monitored by an optical spectrum analyzer (OSA, AQ6370D, YOKOGA WA).

III. EXPERIMENTAL RESULT AND DISCUSSION

A. Fabrication of LPFG with Different Diameters






Fig. 2 Changes in the diameter of the taper region of the tapered FMF, the diameters of the taper waists are: $50-30\mu m$









Fig. 3 Transmission spectrum of FMF at different diameters

The system testing software is used to drive the built-in image processing system of the fusion splicer to scan the surface of the fiber with a resolution of 0.2 mm/s to measure the diameter change of the prepared tapered FMF. Fig. 2 shows the diameter changes of the tapered FMF with a taper waist diameter of $50\text{-}30\mu\text{m}$, and the lengths of each taper region are 1, 4, and 1 cm, respectively.

We fabricated long-period fiber gratings on few-mode fiber of $50\text{-}30\mu m$, respectively. Fig. 3(a) shows the LPFG prepared on a fiber diameter of $50\mu m$ with period of $450\mu m$ and the resonant wavelength is $1493\mu m$. Fig. 3(b) shows the LPFG prepared on a fiber diameter of $40\mu m$. The period of the TMF-LPFG in our experiment is $640\mu m$, the resonant wavelength is $1532.6\mu m$. As shown in Fig.3(c), we fabricated LPFG on the fiber diameter of $30\mu m$ with period of $620\mu m$, the resonant wavelength is $1550\mu m$.

B. SRI Sensing Characteristics of Tapered FMF-LPFG

The refractive index characteristics of 50µm FMF-LPFG in the range of 1.333 to 1.454 were investigated. As shown in Fig.4(a), (b), when the refractive index increased, the resonance wavelength was shifted to shorter wavelength, the resonant wavelength shifted 14 nm to short wavelength, the maximum surrounding refractive index sensitivity were measured to be -320nm/RIU.







Fig. 4 Refractive index sensing characteristics of $50\mu m$ diameter FMF-LPFG

Fig. 5 shows the refractive index characteristics of 40µm FMF-LPFG in the range of 1.333 to 1.448, the resonant wavelength shifted 30 nm to short wavelength, the maximum refractive index sensitivity increased to -4233nm/RIU.

Fig. 6 shows the refractive index characteristics of LPFG prepared on 30um FMF. In the refractive index range of 1.333 to 1.451, the resonant wavelength shifted 97 nm to the short wavelength, and the maximum refractive index sensitivity was -4632nm/RIU.







Fig. 5 Refractive index sensing characteristics of 40μm diameter FMF-






Fig. 6 Refractive index sensing characteristics of 30 μ m diameter FMF-LPFG

We compared the surrounding refractive index sensitivity of LPFGs prepared on optical fibers of different diameters, and through the experimental results, it can be found that under the influence of the same refractive index, as the diameter of the fiber decreases, the evanescent field inside the fiber increases, the resonance peak has a larger wavelength shift to the short wavelength, and the surrounding refractive index sensitivity is higher.

IV. CONCLUSION

In conclusion, we fabricated a tapered FMF refractive index sensor using carbon dioxide laser processing system.

We investigated the SRI characteristics of the tapered FMF-LPFG experimentally, the maximum SRI sensitivity was 4632 nm/RIU in an SRI range from 1.435 to 1.451. As the fiber diameter decreases, the evanescent field inside the fiber increases, The refractive index sensitivity of the fiber will also increase. The proposed sensor based tapered FMF-LPFG has a promising application as a high sensitivity SRI sensor.

REFERENCES.

- Q. Ling and Z. Gu, "Simultaneous detection of SRI and temperature with a FM-LPFG sensor based on dual-peak resonance," J. Opt. Soc. Am. B 36, 2210-2215 (2019).
- [2] J. Dong, M. Sang, Q. Wang, et al. Temperature sensitivity of LPFG inscribed in few modes fiber[C]. //AOPC 2017: Fiber Optic Sensing and Optical Communications. International Society for Optics and Photonics, 2017, 10464: 104640E.
- [3] B. Wang, W. Zhang, Z. Bai, et al. CO₂-Laser-Induced Long Period Fiber Gratings in Few Mode Fibers[J]. IEEE Photonics Technology Letters, 2015, 27(2): 145-148.
- [4] P. Fan, L. Sun, Z. Yu, et al. Higher-order diffraction of long-period microfiber gratings realized by arc discharge method[J]. Optics Express, 2016, 24(22):25380.
- [5] X. Fu, Y. Zhang, Y. Wang, et al. A temperature sensor based on tapered few mode fiber long-period grating induced by CO₂ laser and fusion tapering[J]. Optics & Laser Technology, 2020, 121: 105825.
- [6] Y. Liu, J. Wang, W. Chen et al., "High Sensitivity Refractometer Based on Tapering Two-Mode Fiber Embedded Long-Period Fiber Grating," in IEEE Photonics Technology Letters, vol. 35, no. 3, pp. 136-139, 1 Feb.1, 2023.
- [7] X. Zhao, Y. Zhao, Y. Liu, Z. Liu, C. Mou, L. Shen, L. Zhang, and J.Luo, "High-order mode conversion in a few-mode fiber via laserinscribed long-period gratings at 1.55 μm and 2 μm wavebands," Appl. Opt. 59, 10688-10694 (2020)
- [8] J. Dong, M.Sang, et al., "Refractive Index Sensor Based on Graphene Oxide-Coated Long-Period Fiber Grating Inscribed in a Two-Mode Fiber," in IEEE Access,vol. 8, pp. 109028-109037, 2020, doi: 10.1109/ACCESS. 2020.3001375.