

Glass Surface Detection Grounded in 3D Visual Geometry

Yiwei Lu*
6243112037@stu.jiangnan.edu.cn
Jiangnan University
Wuxi, China

Ke Xu*
kkangwing@gmail.com
University of Science and Technology
of China
Hefei, China

Tao Yan†
yantao.ustc@gmail.com
Jiangnan University
Wuxi, China

Xiaojun Chang
cxj273@gmail.com
University of Science and Technology
of China
Hefei, China

Radu Timofte
radu.timofte@uni-wuerzburg.de
University of Wurzburg
Bayern, Germany

Rynson W. H. Lau
rynsonwhlau@gmail.com
City University of Hong Kong
(Dongguan)
Dongguan, China

Abstract

Glass surface detection (GSD) is critical for scene understanding and reconstruction, and yet remains challenging due to the transparency and reflectivity of glass surfaces. Existing GSD methods typically rely on 2D appearance cues, which may fail in geometrically ambiguous scenes. In this paper, we propose a paradigm shift: grounding GSD in 3D visual geometry to explicitly model the physical existence of glass surfaces. Our method first distills rich 3D priors from the visual geometry grounded transformer (VGGT) and generates glass-aware 3D representations. It then exploits multi-tasking learning with a novel glass detection head, consisting of two core modules: a Frequency Self-Attention Module (FSAM) that identifies glass-specific spectral features for glass surface localization, and a Geometry Grounding Block (GeGB) that selectively grounds 2D features in 3D geometry for glass surface segmentation. Extensive experiments demonstrate that our method achieves state-of-the-art performance across seven standard GSD benchmarks, generalizes well to video/multi-modal data, and substantially improves reconstruction in glass scenes. Code is available in https://github.com/YT3DVision/VGGT_GLASS.

CCS Concepts

- General and reference → General conference proceedings;
- Computing methodologies → Object detection.

Keywords

Glass Surface Detection; Geometry-aware Scene Perception

1 Introduction

Glass is ubiquitous in our daily lives. However, the transparency and specularly of glass create a unique form of semantic and geometric ambiguity for machine perception: the visual data of a glass surface contains both transmitted background scenes and foreground reflections. Such inconsistency violates assumptions of many vision pipelines, *e.g.*, depth/optical flow estimation [23, 32], 3D reconstruction [33, 38], and autonomous navigation [17, 31]. Hence, accurate glass surface detection is essential for robust visual understanding and interactions in the real world.




Figure 1: SOTA GSD methods typically rely on 2D appearance cues (*e.g.*, by explicitly modeling the ghosting effects [36]) or implicitly learning glass-specific embeddings from other modalities (*e.g.*, text) to query large-scale pre-trained image diffusion priors [13]. However, glass surfaces do not always exhibit strong ghosting effects [36]. While the text-based image priors [13] show promising glass surface localization performances, they are not sufficiently discriminative for pixel-wise segmentation. In this work, we propose to shift the paradigm by grounding GSD in large-scale pre-trained 3D visual geometry. We explicitly model the physical existence of glass surfaces, resulting in accurately glass segmentation.

Existing glass surface detection (GSD) methods typically learn appearance cues from the RGB domain (*e.g.*, multiscale contextual features [2, 21, 39], reflections [14, 16], ghosting effects [36], and boundaries [6, 8]) or multi-modalities (combining RGB with, *e.g.*, polarization [20, 24], thermal [11], and depth [15]). Most recently, Li et al. [13] proposed a diffusion-based method to leverage the 2D image priors from large-scale foundation models for GSD. Nonetheless, existing methods are inherently limited to 2D appearance-based reasoning: while effective in localizing glass regions, they tend to fail in segmenting glass surfaces accurately. As shown in Fig. 1 (2nd and 3rd columns), state-of-the-art methods typically produce false positives in surrounding non-glass regions that are visually similar to glass regions.

We observe that humans resolve such visual ambiguity not by scrutinizing image pixels alone, but by constructing and reasoning within a 3D spatial model of the scene, as the intrinsic constraint

*Both authors contributed equally to this research.

†Tao Yan is the corresponding author.

theory [5] suggests: “*human visual systems seek stable 3D interpretations from ambiguous 2D cues*”. Glass surfaces, as physical objects, introduce geometric (e.g., depth and surface normals) and multi-view inconsistencies. This motivates us to propose the paradigm shift, from modeling appearance-based cues to explicitly reasoning scene geometry, directly detecting and interpreting these systematic geometric inconsistencies as reliable signatures of glass surfaces by a 3D-grounded model.

We therefore turn to Visual Geometry Grounded Transformers (VGGT) [28], a foundation model that encodes rich, large-scale 3D prior knowledge. Trained for multi-view reconstruction, VGGT can infer a comprehensive set of 3D attributes, including camera pose, depth, and point clouds, from single images with impressive generalization. However, directly applying VGGT for GSD is non-trivial due to two core challenges: (1) VGGT inherently “sees through” glass, accurately modeling the occluded background while failing to register the glass surface itself, and (2) a fundamental domain gap exists between extracted 3D geometry features and 2D semantic features for pixel-wise glass surface segmentation.

To address these challenges, we propose a novel framework that detects glass surfaces based on a strong 3D vision foundation model. Our approach has two steps. First, we formulate a training pipeline that leverages VGGT to generate pseudo-ground-truth 3D scene representations, and then refine these representations using a planar interpolation strategy to obtain more consistent geometric supervision. Second, we propose a glass detection head with two complementary components: the Frequency Self-Attention Module (FSAM) and the Geometry Grounding Block (GeGB). FSAM captures ambiguous appearance patterns of transparent materials in the frequency domain, providing cues for localizing regions where standard spatial features are unreliable. Building upon this, GeGB incorporates rectified 3D geometric features to produce geometry-aware representations for accurate glass segmentation. Our method is efficiently fine-tuned via Low-Rank Adaptation (LoRA), preserving the foundational 3D knowledge while specialized for GSD. As shown in Fig. 1 (4th column), our method can accurately differentiate glass regions from ambiguous non-glass ones.

In summary, the main contributions of this work include:

- We propose to ground the glass surface detection task in 3D visual geometry and present the first framework that effectively leverages large-scale 3D geometry priors for robust glass surface detection, establishing a new strong baseline.
- We propose a novel glass head with two core modules: FSAM, which learns discriminative glass features in the frequency domain, and GeGB, which adaptively grounds learned 2D appearance features in 3D geometry priors.
- We highlight the effectiveness and geometric awareness of our learned GSD representations through extensive experiments, demonstrating SOTA performances on seven standard benchmarks, strong generalization to multi-modal or video GSD data, and substantial improvements on glass scene reconstruction.

2 Related Work

2.1 Glass Surface Detection (GSD)

Existing deep GSD methods can be broadly categorized into RGB-based and multi-modal approaches. RGB-based methods exploit various appearance cues, such as multiscale contextual features [2, 21, 39], boundary information [6, 8], reflections [14], ghosting effects [36], and temporal information [16, 19, 30], while multimodal methods incorporate additional modalities such as polarization [20, 24], thermal infrared [11], near-infrared [37], and depth [15] to complement the RGB-based appearance cues. Very recently, two GSD methods based on visual foundation models have been proposed. Hao et al. [7] generate large amounts of glass-containing images using the Stable Diffusion model [27] to train the Segment Anything Model (SAM) [12] for GSD, while Li et al. [13] propose the Stable Diffusion-based GSD model.

Despite their success, these methods primarily relying on 2D appearance cues struggle in scenes where glass surfaces do not exhibit distinct visual patterns. In this paper, we show that our method achieves robust detection by grounding GSD in 3D visual geometry.

2.2 Low Rank Adaptation (LoRA)

The rapid scaling of visual foundation models has made parameter-efficient-fine-tuning (PEFT) essential for adapting large pre-trained models to downstream tasks. Among PEFT methods, LoRA [9] emerges as a simple yet highly effective method. Instead of updating all model parameters, LoRA injects learnable low-rank matrices into the linear layers of a frozen backbone, which reduces the number of trainable parameters by orders of magnitude while preserving the pre-trained knowledge. Subsequent works then improve LoRA for reducing memory usage [4] and numbers of trainable parameters [18, 40], improving optimization dynamics [29, 41], and enhancing LoRA’s performance [10, 42]. While these methods offer improvements, the vanilla LoRA formulation remains widely adopted due to its robustness and simplicity.

In our work, we adopt the vanilla LoRA to efficiently adapt the VGGT encoder to leverage 3D geometry priors for GSD. LoRA allows preserving VGGT’s powerful 3D representations while specializing the model for GSD with minimal parameter overhead.

3 Method

We aim to establish a new paradigm for glass surface detection by explicitly grounding this task in 3D geometry. The core insight is that glass surfaces, despite their visual ambiguity, introduce consistent geometric irregularities such as depth inconsistency and multi-view consistency, which can be reliably detected by models with strong 3D scene understanding priors. To this end, we build our method upon the Visual Geometry Grounded Transformer (VGGT) [28] as a foundational source of large-scale 3D priors, and propose a novel method to adapt these priors for glass surfaces detection.

3.1 Pipeline

As shown in Fig. 2, our method contains two steps: (1) generation of rectified 3D pseudo-ground truth and (2) end-to-end multi-tasking




Figure 2: Method Overview. We present a novel two-step approach that grounds glass surface detection in 3D visual geometry. In the first step, we generate rectified 3D pseudo-ground truth of point clouds and depths by leveraging VGGT and ground truth glass surface masks. In the second step, we formulate a multi-task learning objective with a novel glass head for geometry-aware GSD. Our method achieves state-of-the-art GSD performance, generalizes well to video/multi-modal data, and substantially improves reconstruction in glass scenes.




Figure 3: Depth map correction for glass surfaces improves their physical plausibility and geometric coherence.

learning with a novel glass detection head. In the first step, we use VGGT to infer dense depth $\bar{D} \in \mathbb{R}^{H \times W}$ and point cloud $\bar{P} \in \mathbb{R}^{3 \times H \times W}$ from a single RGB image $I \in \mathbb{R}^{3 \times H \times W}$. Since VGGT “sees through” glass surfaces, we rectify the geometry in glass regions via a planar interpolation method based on the ground truth glass mask $\hat{G} \in \mathbb{R}^{H \times W}$ (Sec. 3.2). In the second step, the input image $I \in \mathbb{R}^{3 \times H \times W}$ is encoded by the adapted VGGT backbone (consisting of L frozen frame attention layers with learnable low-rank matrices in the linear layers for Low Rank Adaptation (LoRA)). The extracted features are then processed by three decoders for depth, point cloud, and glass (and edge) prediction. A novel glass head (Sec. 3.3) is proposed to segment glass surfaces and delineate their boundaries based on 3D geometric and 2D appearance features.

3.2 Depth and Point Cloud Correction

VGGT can provide strong geometry priors, but cannot reliably perceive glass surfaces, as it reconstructs the occluded background

rather than the physical glass planes. This results in depths and point clouds that are semantically correct but geometrically inconsistent in the glass regions, thereby introducing misleading signals during training. We address this problem via a geometry-aware correction method that explicitly injects a consistent 3D structure into the glass regions. Our method is motivated by the geometric observation that in most real-world scenes, glass surfaces, despite potential mild curvature, are approximately planar. This allows us to formulate the correction as a planar interpolation problem anchored at the glass boundary, where depth values are reliable in non-glass regions. This ensures that the corrected 3D data reflects both scene geometry and the physical presence of glass, providing coherent multi-modal learning signals for the model.

Specifically, given the initial depth map $\bar{D}$ and point cloud $\bar{P}$ from VGGT, and the ground truth glass mask $\hat{G}$, our method computes the corrected depth $\hat{D}$ and points $\hat{P}$ via:

(1) *Boundary-aware Depth Anchoring.* As pixels at boundaries and corners often lack geometric context, to preserve the global scene layout, we blend the original depth of a corner pixel with that of its nearest non-glass pixel to retain perspective consistency, as:

$$\hat{D}(i, j) = \alpha * \bar{D}(\text{Nearest}(i, j)) + (1 - \alpha) * \bar{D}(i, j), \quad (1)$$

where $i \in \{0, H - 1\}$ and $j \in \{0, W - 1\}$ denote corner pixel coordinates, and $\text{Nearest}(\cdot)$ returns the coordinates of the nearest non-glass pixel to (i, j) . α is set to 0.8 to bias the correction toward geometrically reliable non-glass regions.

(2) *Planar Interpolation within Glass Regions.* For an interior glass pixel (i, j) , we model the local glass region as a plane defined by nearest non-glass depths along the horizontal and vertical directions. Let the pixel’s vertical bounds be a, b and horizontal bounds c, d , where $\bar{D}(a, j), \bar{D}(b, j), \bar{D}(i, c), \bar{D}(i, d)$ are depths from nearest

non-glass pixels along the respective directions. We compute the corrected depth $\hat{D}(i, j)$ as:

$$\hat{D}_v(i, j) = \bar{D}(a, j) + \frac{i-a}{b-a}(\bar{D}(b, j) - \bar{D}(a, j)), \quad (2)$$

$$\hat{D}_h(i, j) = \bar{D}(i, c) + \frac{j-c}{d-c}(\bar{D}(i, d) - \bar{D}(i, c)), \quad (3)$$

$$\hat{D}(i, j) = 0.5 * \hat{D}_v(i, j) + 0.5 * \hat{D}_h(i, j). \quad (4)$$

Examples of the corrected depths are shown in Fig. 3. The corrected depths $\hat{D}$ are combined with initial point clouds $\bar{P}$ to produce $\hat{P}$.




Figure 4: Our Glass Head for precise glass surface segmentation and glass boundary delineation is built upon (1) the Frequency Self-Attention Module (FSAM) for capturing discriminative spectral representation of glass, and (2) the Geometry Grounding Block (GeGB) that reduces visual ambiguities via geometry-aware feature alignment and selective fusion.

3.3 Glass Detection Head

We propose a novel glass detection head for precise glass surface segmentation and glass boundary delineation, based on two physically-grounded modules: a Frequency Self-Attention Module (FSAM) that captures glass-specific 2D visual features, and a Geometry Grounding Block (GeGB) that integrates 3D geometry features with 2D visual features for glass segmentation.

As shown in Fig. 4, we first extract multi-scale token representations from the VGGT encoder at {4th, 11th, 17th, 23rd} layers. We assign FSAM at each scale to learn glass-aware appearance features $\{F^i_{glass}\}_{i=1}^4$. F^i_{glass} is directly used for the deepest decoding stage, whereas the other features are then enriched with multi-modal point and depth features (F_{point}, F_{depth}) via the GeGB, yielding the fused feature $\{F^i_f\}_{i=1}^3$. Then, the decoder takes $\{F^i_f\}_{i=1}^3$ as input and produces the decoded feature $\{F^i_{de}\}_{i=1}^3$ to predict multi-scale glass surface masks $\{G^i\}_{i=1}^3$ and glass boundary maps $\{B^i\}_{i=1}^3$. Finally, F^1_{de} are further refined by passing through the GeGB and decoder again to produce more fine-grained results.

Frequency Self-Attention Module (FSAM). Glass surfaces introduce subtle yet consistent appearance distortions due to light absorption, scattering, and refraction. Such glass-induced attenuation typically reduces local contrast and results in a characteristic high-frequency suppression that is largely irrelevant to the scene content. We capture such appearance cues via FSAM in the frequency domain to preliminarily localize glass regions. Unlike standard spatial-domain self-attention, which may fail to distinguish glass features from complex backgrounds, our FSAM operates in the frequency domain




Figure 5: Our Frequency Self-Attention Module (FSAM) operates in the frequency domain to capture prominent spectral features of glass surfaces for their preliminary localization.

to characterize the prominent spectral features inherent to glass surfaces.

As shown in Fig. 5, the extracted token representations at i -th scale, denoted as $\{T^i\}_{i=1}^4$, are first projected to a lower-dimensional space via a linear layer to reduce computational cost. This process yields $\{F^i_{in}\}_{i=1}^4 \in \mathbb{R}^{N \times C}$, where the output channel dimension is set to $C = 2^{i+5}$. For each channel of F^i_{in} , we compute its amplitude spectrum via 1D Fast Fourier Transform (FFT) as follows:

$$F_{fre} = |\text{FFT}(F_{in})|. \quad (5)$$

We then project F_{fre} into query and key matrices via $W_Q(\cdot)$ and $W_K(\cdot)$, and compute the attention map:

$$\text{Atten} = \text{Softmax}\left(\frac{W_Q(F_{fre}) \times W_K(F_{fre})^T}{\sqrt{C}}\right). \quad (6)$$

The frequency-domain attention map Atten is then applied to the original spatial features F_{in} , followed by layer normalization and residual connection:

$$F_{out} = \text{LN}(\text{Atten} \times W_V(F_{in})) + F^i_{in}, \quad (7)$$

where $W_V(\cdot)$ projects F_{in} into value matrix. This formulation effectively circumvents the quantization error often caused by 1D Inverse Fast Fourier Transform (IFFT) and retains spatial information through residual connections. Finally, the feature F_{out} is re-shaped and processed via convolution and transposed convolution to produce the glass features F_{glass} with aligned spatial and channel dimensions.

Geometry Grounding Block (GeGB). While depth and point clouds both encode 3D geometry, they provide complementary information: depth maps offer dense pixel-aligned distance estimations, whereas point clouds capture local surface structures and provide volumetric context. Incorporating both modalities ensures that glass features are grounded in a comprehensive 3D scene representation.

To this end, we design a symmetrical gating-based geometry grounding block to incorporate both depth and point cloud features, as shown in Fig. 6a. For each geometry modality $m \in \{\text{depth}, \text{point}\}$, we first compute a spatial attention map that highlights regions where geometric features are discriminative as follows:

$$\text{SA}(F_m) = \sigma(\text{Conv}_7([\text{Mean}(F_m), \text{Max}(F_m)])), \quad (8)$$

where $\text{Mean}(\cdot)$ and $\text{Max}(\cdot)$ compute the channel-wise average and maximum values, respectively, $[\cdot, \cdot]$ indicates feature concatenation,




Figure 6: (a) Our Geometry Grounding Block (GeGB) incorporates depths and points as complementary geometric context for reasoning glass regions, and (b) our Decoder Block for segmenting glass regions and delineating their boundaries.

and σ is sigmoid activation. We then enrich each geometry modality with glass appearance features via a parallel enhancement path:

$$F_{mm} = \text{CBAM}(\text{Conv}_3([F_m, F_{glass}^i \odot \text{SA}(F_m)])), \quad (9)$$

where F_{mm} is either enhanced depth features F_{spa} or point features F_{geo} , and CBAM [34] is used to refine features via channel and spatial attention. We leverage the coarse glass surface prediction G^{i+1} from the previous decoder layer to guide the multi-modal fusion of F_{glass}^i , F_{spa} , and F_{geo} , as follows:

$$F_f^i = \text{Conv}_1[F_{glass}^i, G^{i+1} \odot F_{spa}, G^{i+1} \odot F_{geo}], \quad (10)$$

where $\odot$ is element-wise multiplication.

Decoder Block. As shown in Fig. 6b, the decoder layer at each scale processes the F_f^i and the F_{de}^{i+1} from the previous layer via a standard residual block to produce F_{de}^i . We assign a 1×1 convolution layer to generate the glass mask and a 3×3 convolution layer to delineate glass boundaries.

3.4 Multi-Modal Loss Function

We use a hybrid multi-task loss to train our network:

$$\mathcal{L} = \mathcal{L}_g + \mathcal{L}_b + \lambda \mathcal{L}_d + \lambda \mathcal{L}_p, \quad (11)$$

where λ is a balancing hyper-parameter empirically set to 0.1. For geometry prediction, we adopt the same depth loss $\mathcal{L}_d$ and point cloud loss $\mathcal{L}_p$ as defined in VGGT [28]:

$$\mathcal{L}_d = \|C_d \odot (D - \hat{D})\| + \|C_d \odot (\nabla D - \nabla \hat{D})\| - \log C_d, \quad (12)$$

$$\mathcal{L}_p = \|C_p \odot (P - \hat{P})\| + \|C_p \odot (\nabla P - \nabla \hat{P})\| - \log C_p, \quad (13)$$

where C_d and C_p are the predicted confidence maps for depths and points, respectively. D and P are the predicted depth maps and point clouds, while $\hat{D}$ and $\hat{P}$ are our rectified pseudo ground truth depth and point. ∇ computes gradients and $\odot$ is element-wise product.

For glass surface predictions, we employ BCE loss [3] and IoU loss [25] at the pixel- and region-level, respectively. Given the glass prediction $\{G^i\}_{i=0}^3$ and its corresponding ground truth mask $\hat{G}$,

$\mathcal{L}_{glass}$ is defined as:

$$\mathcal{L}_{glass}(G, \hat{G}) = \mathcal{L}_{bce}(G, \hat{G}) + \mathcal{L}_{iou}(G, \hat{G}), \quad (14)$$

$$\mathcal{L}_g = \sum_{i=1}^4 \frac{\mathcal{L}'_{glass}(G^i, \hat{G})}{2^{i-1}} + \mathcal{L}'_{glass}(G^c, \hat{G}), \quad (15)$$

where G^c is the glass surface mask derived from the point cloud and depth features (*i.e.*, concatenation of F_{depth} and F_{point} followed by 1×1 convolution and Sigmoid activation), which facilitates the training via granular supervisions on geometry features.

For glass boundary predictions, $\mathcal{L}_b$ is defined in a similar way to $\mathcal{L}_g$, except that we replace the IoU loss with the Dice loss [22].

4 Experiments

4.1 Experimental Setups

Implementation Details. Our framework is implemented with PyTorch on a single NVIDIA RTX 4090 GPU (24GB). We follow VGGT to use $L = 24$ frame attention layers for feature extraction, where Low Rank Adaptation (LoRA) is applied to each frame attention layer with two low-rank matrices, $A \in \mathbb{R}^{d \times r}$ and $B \in \mathbb{R}^{r \times k}$ ($r \ll \min(d, k)$). We set the rank r to 16. Images are resized to 518×518 for training and evaluation. We train our model on a Union training set, which combines the training sets from GDD [21], GSD [14], Trans10K-Stuff [35], and HSO [39]. We employ the Adam optimizer with a learning rate of 1×10^{-4} and a batch size of 4. The training process spans 80 epochs.

Evaluation Methods, Datasets, and Metrics. We compare to nine existing GSD methods, including six single-image-based ones (GDNet [21], GSDNet [14], EBLNet [8], RFENet [6], GhostingNet [36] and GlassWizard [13]), two multi-modal methods (RGB-Thermal [11] and RGB-Depth [15]), two video GSD methods (VGSDNet [16] and MVGDNet [19]). We include three foundation models (SAM2 [26], VGGT [28], and SAM3 [1]) as baselines. For VGGT, we used the same segmentation decoder as ours.

We evaluate on seven standard benchmarks, including four single-image-based datasets (GDD [21], GSD [14], HSO [39] and Trans10k-stuff [35]), two multi-modal GSD dataset (RGB-Thermal-based [11] and RGB-Depth-based [15]), and the video-based VGSD-D dataset [16].

We report five standard evaluation metrics, including Intersection over Union (IoU $\uparrow$), F-measure ($F_\beta\uparrow$), Mean Absolute Error (MAE $\downarrow$), Balanced Error Rate (BER $\downarrow$), and Accuracy (ACC $\uparrow$).

4.2 Comparisons to SOTA Methods

Single-Image GSD Results. We first compare our method against six SOTA single-image GSD methods (GDNet, GSDNet, EBLNet, RFENet, GhostingNet, and GlassWizard) and three foundation models (SAM2, VGGT, and SAM3), on four standard benchmarks (GDD, GSD, HSO, and Trans10K-Stuff). For a fair comparison, all competing methods are retrained under identical training settings.

The results reported in Tab. 1 and 2 demonstrate that our method maintains a clear performance advantage across all evaluated datasets and metrics. Notably, our method consistently outperforms the latest GhostingNet that relies on 2D ghosting cues and GlassWizard that leverages large-scale 2D diffusion priors, demonstrating the advantage of grounding GSD task in 3D visual geometry.

Table 1: Quantitative comparison between our method and existing GSD methods on standard single-image datasets. Foundation-model baselines are also included for reference. Best results are marked in bold.

Methods	Venue	GDD [21]					GSD [14]					HSO [39]				
		IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$	IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$	IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$
SAM2	-	82.70	0.891	0.090	8.44	0.920	73.00	0.797	0.096	9.24	0.917	71.18	0.801	0.134	12.04	0.898
VGGT	CVPR'25	85.26	0.914	0.072	6.68	0.948	78.63	0.868	0.065	7.02	0.930	77.62	0.854	0.094	8.35	0.944
SAM3	ICLR'26	92.88	0.966	0.034	3.04	0.974	89.64	0.943	0.033	3.02	0.988	87.24	0.931	0.054	4.66	0.965
GDNet	CVPR'20	88.71	0.934	0.059	5.49	0.961	83.00	0.893	0.055	5.68	0.952	79.25	0.871	0.093	8.65	0.931
GSDNet	CVPR'21	88.52	0.935	0.057	5.29	0.951	82.96	0.895	0.052	6.00	0.938	80.17	0.880	0.085	8.07	0.928
EBLNet	ICCV'21	88.02	0.932	0.059	5.51	0.950	82.25	0.894	0.056	5.88	0.936	80.53	0.887	0.082	7.79	0.927
RFENet	IJCAI'23	88.04	0.920	0.061	6.02	0.975	81.26	0.869	0.049	6.17	0.961	78.49	0.852	0.095	8.78	0.950
GhostingNet	TPAMI'25	91.19	0.954	0.044	3.98	0.964	86.69	0.923	0.042	4.19	0.972	82.97	0.903	0.073	6.79	0.942
GlassWizard	ICCV'25	93.30	0.969	0.039	3.62	0.967	90.40	0.952	0.036	4.52	0.969	87.90	0.941	0.055	5.44	0.952
Ours	-	95.56	0.981	0.021	1.88	0.988	91.91	0.962	0.022	2.24	0.989	92.04	0.963	0.031	2.73	0.984

Table 2: Quantitative comparison on the Trans10k-stuff. Best results are marked in bold.

Methods	Venue	Trans10k-stuff [35]				
		IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$
SAM2	-	81.16	0.884	0.075	6.59	0.956
VGGT	CVPR'25	84.86	0.912	0.060	5.39	0.963
SAM3	ICLR'26	91.07	0.956	0.033	2.82	0.984
GDNet	CVPR'20	88.30	0.937	0.047	4.08	0.976
GSDNet	CVPR'21	88.62	0.940	0.043	3.87	0.974
EBLNet	ICCV'21	88.35	0.939	0.046	4.04	0.971
RFENet	IJCAI'23	86.51	0.912	0.053	4.84	0.992
GhostingNet	TPAMI'25	89.72	0.948	0.038	3.40	0.979
GlassWizard	ICCV'25	92.80	0.965	0.030	3.04	0.979
Ours	-	93.85	0.974	0.022	1.76	0.994

Table 3: Comparisons to multi-modal GSD methods, i.e., RGB-Thermal [11] (upper) and RGB-Depth [15] (lower) on their proposed datasets. Best results are in bold.

Methods	Venue	IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$
RGB-Thermal	TIP'23	93.80	0.965	0.027	4.08	-
Ours	-	95.71	0.976	0.023	4.19	0.970
RGB-Depth	AAAI'25	74.20	0.853	0.043	9.30	-
Ours	-	81.23	0.873	0.026	7.05	0.880

Generalization Results. We evaluate our method’s generalization capability by directly testing on two multi-modal GSD datasets (RGB-Thermal [11] and RGB-Depth [15]) and the video GSD dataset VGSD-D [16]. Tab. 3 reports the comparisons with multi-modal methods. Without requiring additional thermal or depth sensors, Our method achieves comparable performance to RGB-Thermal methods (Tab. 3 (top part)) while outperforming RGB-Depth methods (Tab. 3 (bottom part)). Tab. 4 further reports the comparisons on the VGSD-D. GhostingNet often degrades when ghosting cues are weak or ambiguous, whereas GlassWizard achieves

Table 4: Comparisons on the video GSD dataset VGSD-D [16]. Best results are in bold.

Methods	Venue	IoU $\uparrow$	$F_\beta\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$
VGSDNet	AAAI'24	80.72	0.885	0.099	9.60	0.898
GhostingNet	TPAMI'25	80.40	0.888	0.100	9.30	0.905
GlassWizard	ICCV'25	94.20	-	0.031	2.92	-
MVGSDNet	AAAI'26	86.54	0.925	0.064	6.10	0.935
Ours	-	97.36	0.982	0.016	1.97	0.986

stronger performance by leveraging large-scale 2D diffusion priors. Nevertheless, our method consistently outperforms GlassWizard across all evaluation metrics.

Visual Results. We provide visual comparisons with single-image-based GSD methods in Fig. 7. We can see that previous methods relying on 2D appearance cues may easily over- or under-detect glass regions that exhibit less distinct cues (e.g., reflections) and have similar visual patterns to those of non-glass regions, even with large-scale pre-trained 2D diffusion priors. In contrast, our method achieves accurate glass surface segmentation, clearly distinguishing glass from non-glass regions, as demonstrated in the first four examples. In addition, we showcase two challenging examples: a scene fully covered by glass (the fifth example) and a scene where the glass region is partially occluded by objects (the last example). While these two examples generally fail existing methods, our method can still accurately segment the glass surfaces and delineate their boundaries. These visual results highlight that 3D scene geometry information is vital for robust GSD.

Application. To further demonstrate the effectiveness of our geometry-aware representation, we evaluate its impact on 3D reconstruction in scenes containing glass surfaces. As shown in Fig. 8, the original VGGT [28] tends to reconstruct the 3D structure of objects behind transparent surfaces, often neglecting the physical presence of glass. In contrast, our method explicitly incorporates planar geometric priors of glass surfaces, leading to more accurate reconstruction in glass regions. Exploring more expressive representations for multi-layered point cloud reconstruction remains an interesting direction for future work.



Figure 7: Visual comparison between our method and single-image GSD methods, which highlights that 3D scene geometry information is vital for robust glass surface detection.




Figure 8: Visual comparison between VGGT [28] and our method in monocular depth estimation and reconstruction of 3D scenes with glass surfaces.

4.3 Ablation Studies


We conduct ablation studies based on the Union glass test set (which combines the test sets from GDD, GSD, Trans10K-Stuff, and HSO) to study their broader impact on the GSD task instead of individual datasets. Tab. 5 reports the results.

Model Designs. As shown in Tab. 5 (top part), we first analyze network components by removing each component individually

and retraining the ablated model, denoted as “w/o LoRA”, “w/o FSAM”, and “w/o GeGB”. We also remove Eq. 5 in FSAM (which then becomes a standard spatial-domain self-attention mechanism) and denote it as “w/o FFT”. We also apply the self-attention mechanism completely in the frequency domain, *i.e.*, replacing F_{in} with F_{fre} in Eq. 7 and denote it as “ $F_{in} \rightarrow F_{fre}$ ”. In addition, we also remove the depth and point paths individually from our GeGB, denoted as

Table 5: Ablation results of our method.

Methods	IoU $\uparrow$	F β $\uparrow$	MAE $\downarrow$	BER $\downarrow$	ACC $\uparrow$
w/o LoRA	88.27	0.931	0.046	4.05	0.981
w/o FSAM	92.78	0.964	0.027	2.29	0.988
w/o GeGB	92.67	0.963	0.027	2.31	0.988
w/o FFT	92.82	0.967	0.027	2.37	0.986
$F_{in} \rightarrow F_{fre}$	93.06	0.967	0.026	2.12	0.991
w/o Depth	92.86	0.967	0.026	2.28	0.988
w/o Point	92.70	0.965	0.027	2.25	0.990
w/o P&D-C	93.04	0.965	0.028	2.36	0.985
w/o P-C	92.84	0.963	0.029	2.43	0.984
w/o D-C	92.76	0.962	0.029	2.40	0.987
w/o G^c	92.98	0.968	0.026	2.24	0.988
w/o $\mathcal{L}_b$	92.75	0.967	0.026	2.43	0.983
VGGT $\rightarrow$ SAM3	92.34	0.960	0.030	2.51	0.985
Ours	93.24	0.969	0.025	2.15	0.989

**Figure 9: The visual comparison of different ablated models.**

“w/o Depth” and “w/o Point”, respectively. These ablated models tend to yield sub-optimal performance. Notably, while “ $F_{in} \rightarrow F_{fre}$ ” produces slightly better BER and accuracy results, it leads to a relatively larger IoU performance drop, which shows that completely relying on frequency information tends to over-detect glass regions. These results generally verify the effectiveness of our model designs. Visual comparisons are shown in Fig. 9. FSAM captures semantic cues for glass localization, while GeGB leverages geometric structure to resolve appearance ambiguities.

Training Formulations. As reported in Tab. 5 (middle part), we analyze different learning strategies. We first directly use the VGGT’s original depth and point cloud predictions as supervision (denoted as “w/o P&D-C”). We also use our corrected depths and point clouds as supervision separately, denoted as “w/o P-C” and “w/o D-C”, respectively. In addition, we also remove the glass surface supervision on the geometric features by removing G^c from the $\mathcal{L}_g$ and $\mathcal{L}_b$ in Eq. 11 (denoted as “w/o G^c ”). Last, we remove the glass boundary delineation, which is denoted as “w/o $\mathcal{L}_b$ ”. These degraded results demonstrate the necessity of our training objective formulation. Although the depth interpolation strategy brings marginal improvements, the consistent gains indicate that our model can effectively exploit more accurate 3D supervision when available.

Geometry vs. Semantics. While we demonstrate the superiority of geometric context over large-scale pre-trained diffusion priors, we are interested in whether it can outperform large-scale pre-trained semantic priors. To this end, we replace our VGGT-based encoder with the SAM3 image encoder [1], a large foundation model


for concept segmentation. Note that we also apply LoRA to the SAM3 encoder for a fair comparison (denoted as “VGGT $\rightarrow$ SAM3”). The results in Tab. 5 (bottom part) show that, despite being powerful for general object segmentation, the semantic contexts from SAM3 are still less effective than our geometric contexts for GSD.

4.4 Runtime Efficiency

We compare the number of parameters, GFLOPs, and the averaged inference time of our model, GhostingNet, GlassWizard, and our SAM3-based baseline, using a single NVIDIA RTX 4090 GPU. Tab. 6 reports the results, which show that compared with diffusion-based and SAM3-based methods, our method enjoys a reasonable runtime efficiency and can run interactively (around 8.5 FPS). For details on the computational efficiency of each module, please refer to the supplementary materials.

Table 6: Runtime efficiency comparison on a single NVIDIA RTX 4090 GPU.

Methods	Param(M)	FLOPS(G)	Time(ms)
GhostingNet	271.53	321.70	32.94
GlassWizard	1189.73	890.78	177.00
SAM3-based	471.18	2539.06	134.90
VGGT	989.17	1657.69	159.73
Ours	684.37	1260.67	117.31

**Figure 10: A failure case. Our method may fail when the glass surface (e.g., the windshield) is too close to the camera, providing insufficient surrounding geometric contexts.**

5 Conclusion

In this paper, we have proposed a novel framework that grounds the glass surface detection task in 3D visual geometry. Our approach first exploits rich 3D prior knowledge from the visual geometry foundation model and generates pseudo-ground-truth depths and points in glass regions to strengthen their physical existence. We then formulate a multi-tasking training objective with a novel glass detection head. The glass detection head employs two core modules: FSAM for characterizing glass surfaces as high-frequency attenuation and GeGB for grounding 2D frequency features with 3D geometric features. The proposed model has achieved new SOTA performance across seven standard benchmarks and demonstrated strong generalization capability. It can also run interactively (around 8.5 FPS) on a single consumer-level GPU card.

Our method does have limitations. While our model relies on high-quality 3D visual geometry cues, it may fail when the inferred geometric contexts are limited as shown in Fig. 10, where the windshield is too close to the camera.

Acknowledgments

This work was supported by the National Natural Science Foundation of China (Grant No. 61902151).

References

- [1] Nicolas Carion, Laura Gustafson, Yuan-Ting Hu, Shoubhik Debnath, Ronghang Hu, Didac Suris, et al. 2026. SAM 3: Segment Anything with Concepts. In *ICLR*.
- [2] Qianyu Cheng, Huankang Guan, and Rynson W.H. Lau. 2026. Multi-Semantic Modeling for Glass Surface Detection in the Wild. In *AAAI*.
- [3] Pieter-Tjerk De Boer, Dirk P Kroese, Shie Mannor, and Reuven Y Rubinstein. 2005. A tutorial on the cross-entropy method. *Annals of Operations Research* (2005).
- [4] Tim Dettmers, Artidoro Pagnoni, Ari Holtzman, and Luke Zettlemoyer. 2023. Qlora: Efficient finetuning of quantized llms. In *NeurIPS*.
- [5] Fulvio Domini. 2023. The case against probabilistic inference: a new deterministic theory of 3D visual processing. *Philosophical Transactions of the Royal Society B* (2023).
- [6] Ke Fan, Changan Wang, Yabiao Wang, Chengjie Wang, Ran Yi, and Lizhuang Ma. 2023. RFENet: Towards Reciprocal Feature Evolution for Glass Segmentation. In *IJCAI*.
- [7] Jing Hao, Moyun Liu, Jinrong Yang, and Kuo Feng Hung. 2025. GEM: Boost simple network for glass surface segmentation via vision foundation models. *IEEE TMM* (2025).
- [8] Hao He, Xiangtai Li, Guangliang Cheng, Jianping Shi, Yunhai Tong, Gaofeng Meng, Véronique Prinet, and Lubin Weng. 2021. Enhanced Boundary Learning for Glass-like Object Segmentation. In *ICCV*.
- [9] Edward J Hu, Yelong Shen, Phillip Wallis, Zeyuan Allen-Zhu, Yuanzhi Li, Shean Wang, Lu Wang, and Weizhu Chen. 2022. LoRA: Low-Rank Adaptation of Large Language Models. In *ICLR*.
- [10] Qiushi Huang, Tom Ko, Zhan Zhuang, Lilian Tang, and Yu Zhang. 2025. HiRA: Parameter-efficient hadamard high-rank adaptation for large language models. In *ICLR*.
- [11] Dong Huo, Jian Wang, Yiming Qian, and Yee-Hong Yang. 2023. Glass segmentation with RGB-thermal image pairs. *IEEE TIP* (2023).
- [12] Alexander Kirillov, Eric Mintun, Nikhila Ravi, Hanzi Mao, Chloe Rolland, Laura Gustafson, Tete Xiao, Spencer Whitehead, Alexander C Berg, Wan-Yen Lo, et al. 2023. Segment anything. In *ICCV*.
- [13] Wenxue Li, Tian Ye, Xinyu Xiong, Jinbin Bai, Feilong Tang, Wenxuan Song, Zhaoxu Xing, Lie Ju, Guanbin Li, and Lei Zhu. 2025. GlassWizard: Harvesting Diffusion Priors for Glass Surface Detection. In *ICCV*.
- [14] Jiaying Lin, Zebang He, and Rynson W.H. Lau. 2021. Rich Context Aggregation With Reflection Prior for Glass Surface Detection. In *CVPR*.
- [15] Jiaying Lin, Yuen-Hei Yeung, Shuquan Ye, and Rynson W.H. Lau. 2025. Leveraging RGB-D Data with Cross-Modal Context Mining for Glass Surface Detection. In *AAAI*.
- [16] Fang Liu, Yuhao Liu, Jiaying Lin, Ke Xu, and Rynson WH Lau. 2024. Multi-View Dynamic Reflection Prior for Video Glass Surface Detection. In *AAAI*.
- [17] Ligang Liu, Xi Xia, Han Sun, Qi Shen, Juzhan Xu, Bin Chen, Hui Huang, and Kai Xu. 2018. Object-aware guidance for autonomous scene reconstruction. *ACM TOG* (2018).
- [18] Shih-Yang Liu, Chien-Yi Wang, Hongxu Yin, Pavlo Molchanov, Yu-Chiang Frank Wang, Kwang-Ting Cheng, and Min-Hung Chen. 2024. Dora: Weight-decomposed low-rank adaptation. In *ICML*.
- [19] Yiwei Lu, Hao Huang, and Tao Yan. 2026. MVGDNet: A Novel Motion-aware Video Glass Surface Detection Network. In *AAAI*.
- [20] Haiyang Mei, Bo Dong, Wen Dong, Jiayi Yang, Seung-Hwan Baek, Felix Heide, Pieter Peers, Xiaopeng Wei, and Xin Yang. 2022. Glass segmentation using intensity and spectral polarization cues. In *CVPR*.
- [21] Haiyang Mei, Xin Yang, Yang Wang, Yuanyuan Liu, Shengfeng He, Qiang Zhang, Xiaopeng Wei, and Rynson W.H. Lau. 2020. Don't Hit Me! Glass Detection in Real-World Scenes. In *CVPR*.
- [22] Fausto Milletari, Nassir Navab, and Seyed-Ahmad Ahmadi. 2016. V-net: Fully convolutional neural networks for volumetric medical image segmentation. In *3DV*.
- [23] Matteo Poggi and Fabio Tosi. 2025. FlowSeek: Optical Flow Made Easier with Depth Foundation Models and Motion Bases. In *ICCV*.
- [24] Yu Qiao, Bo Dong, Ao Jin, Yu Fu, Seung-Hwan Baek, Felix Heide, Pieter Peers, Xiaopeng Wei, and Xin Yang. 2023. Multi-view spectral polarization propagation for video glass segmentation. In *ICCV*.
- [25] Xuebin Qin, Zichen Zhang, Chenyang Huang, Chao Gao, Masood Dehghan, and Martin Jagersand. 2019. Basnet: Boundary-aware salient object detection. In *CVPR*.
- [26] Nikhila Ravi, Valentin Gabeur, Yuan-Ting Hu, Ronghang Hu, Chaitanya Ryali, Tengyu Ma, et al. 2024. SAM 2: Segment Anything in Images and Videos. *arXiv:2408.00714* (2024).
- [27] Robin Rombach, Andreas Blattmann, Dominik Lorenz, Patrick Esser, and Björn Ommer. 2022. High-resolution image synthesis with latent diffusion models. In *CVPR*.
- [28] Jianyuan Wang, Minghao Chen, Nikita Karaev, Andrea Vedaldi, Christian Rupprecht, and David Novotny. 2025. VGGT: Visual Geometry Grounded Transformer. In *CVPR*.
- [29] Shaowen Wang, Linxi Yu, and Jian Li. 2024. Lora-ga: Low-rank adaptation with gradient approximation. In *NeurIPS*.
- [30] Zhen Wang, Dongyuan Li, Yaozu Wu, Peide Zhu, Shiyin Tan, and Renhe Jiang. 2025. Video-based Transparent Object Segmentation via Temporal Feature Aggregation. In *ACMMM*. 296–304.
- [31] Kasun Weerakoon, Adarsh Jagan Sathyamoorthy, Mohamed Elnoor, Anuj Zore, and Dinesh Manocha. 2024. TOPGN: Real-time Transparent Obstacle Detection using Lidar Point Cloud Intensity for Autonomous Robot Navigation. *arXiv:2408.05608* (2024).
- [32] Hongyu Wen, Yiming Zuo, Venkat Subramanian, Patrick Chen, and Jia Deng. 2025. Seeing and Seeing Through the Glass: Real and Synthetic Data for Multi-Layer Depth Estimation. In *ICCV*.
- [33] Thomas Whelan, Michael Goesele, Steven J. Lovegrove, Julian Straub, Simon Green, Richard Szeliski, Steven Butterfield, Shobhit Verma, and Richard Newcombe. 2018. Reconstructing scenes with mirror and glass surfaces. *ACM TOG* (2018).
- [34] Sanghyun Woo, Jongchan Park, Joon-Young Lee, and In So Kweon. 2018. CBAM: Convolutional Block Attention Module. In *ECCV*.
- [35] Enze Xie, Wenjia Wang, Wenhai Wang, Mingyu Ding, Chunhua Shen, and Ping Luo. 2020. Segmenting Transparent Objects in the Wild. In *ECCV*.
- [36] Tao Yan, Jiahui Gao, Ke Xu, Xiangjie Zhu, Hao Huang, Helong Li, Benjamin Wah, and Rynson W.H. Lau. 2025. GhostingNet: A Novel Approach for Glass Surface Detection With Ghosting Cues. *IEEE TPAMI* (2025).
- [37] Tao Yan, Shufan Xu, Hao Huang, Helong Li, Lu Tan, Xiaojun Chang, and Rynson WH Lau. 2024. NRGlassNet: Glass surface detection from visible and near-infrared image pairs. *Knowledge-Based Systems* (2024).
- [38] Mao Ye, Yu Zhang, Ruigang Yang, and Dinesh Manocha. 2015. 3d reconstruction in the presence of glasses by acoustic and stereo fusion. In *CVPR*.
- [39] Letian Yu, Haiyang Mei, Wen Dong, Ziqi Wei, Li Zhu, Yuxin Wang, and Xin Yang. 2022. Progressive Glass Segmentation. *IEEE TIP* (2022).
- [40] Longteng Zhang, Lin Zhang, Shaohuai Shi, Xiaowen Chu, and Bo Li. 2023. Lora-fa: Memory-efficient low-rank adaptation for large language models fine-tuning. *arXiv:2308.03303* (2023).
- [41] Qingru Zhang, Minshuo Chen, Alexander Bukharin, Pengcheng He, Yu Cheng, Weizhu Chen, and Tuo Zhao. 2023. Adaptive Budget Allocation for Parameter-Efficient Fine-Tuning. In *ICLR*.
- [42] Zhan Zhuang, Xiequn Wang, Wei Li, Yulong Zhang, Qiushi Huang, Shuhao Chen, Xuehao Wang, Yanbin Wei, Yuhe Nie, Kede Ma, Yu Zhang, and Ying Wei. 2025. Come Together, But Not Right Now: A Progressive Strategy to Boost Low-Rank Adaptation. In *ICML*.