


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	427.02506	2.55536	305.01790	51.24200	0.06084
Mean	427.02506	2.55536	305.01790	51.24200	0.06084
Standard Deviation	-----	-----	-----	-----	-----