


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	516.61683	5.71273	369.01202	61.99300	0.13602
Mean	516.61683	5.71273	369.01202	61.99300	0.13602
Standard Deviation	-----	-----	-----	-----	-----