


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	437.49990	0.97249	312.49993	52.49900	0.02315
Mean	437.49990	0.97249	312.49993	52.49900	0.02315
Standard Deviation	-----	-----	-----	-----	-----