


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	446.12555	1.67657	317.35127	53.31400	0.03992
Mean	446.12555	1.67657	317.35127	53.31400	0.03992
Standard Deviation	-----	-----	-----	-----	-----