


Silicone rubber

Tensile test of silicone rubber elastomers



| | Extension at Maximum Tensile extension (mm) | Load at Maximum Tensile extension (N) | Tensile strain at Maximum Tensile extension (%) | Time at Maximum Tensile extension (sec) | Tensile stress at Maximum Tensile extension (MPa) |
|--------------------|---------------------------------------------|---------------------------------------|-------------------------------------------------|-----------------------------------------|---------------------------------------------------|
| 1 | 400.58327 | 1.56350 | 286.13091 | 48.06900 | 0.03723 |
| Mean | 400.58327 | 1.56350 | 286.13091 | 48.06900 | 0.03723 |
| Standard Deviation | ----- | ----- | ----- | ----- | ----- |