


Silicone rubber

Tensile test of silicone rubber elastomers



| | Extension at Maximum Tensile extension (mm) | Load at Maximum Tensile extension (N) | Tensile strain at Maximum Tensile extension (%) | Time at Maximum Tensile extension (sec) | Tensile stress at Maximum Tensile extension (MPa) |
|--------------------|---|---------------------------------------|---|---|---|
| 1 | 416.93338 | 2.16775 | 297.80955 | 50.03100 | 0.05161 |
| Mean | 416.93338 | 2.16775 | 297.80955 | 50.03100 | 0.05161 |
| Standard Deviation | ----- | ----- | ----- | ----- | ----- |