


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	464.41671	2.40523	331.72622	55.72900	0.05727
Mean	464.41671	2.40523	331.72622	55.72900	0.05727
Standard Deviation	-----	-----	-----	-----	-----