


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	418.34175	2.41660	298.81554	50.20000	0.05754
Mean	418.34175	2.41660	298.81554	50.20000	0.05754
Standard Deviation	-----	-----	-----	-----	-----