


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	560.29163	19.78856	400.20833	67.23400	0.47116
Mean	560.29163	19.78856	400.20833	67.23400	0.47116
Standard Deviation	-----	-----	-----	-----	-----