


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	477.54165	2.06716	341.10117	57.30400	0.04922
Mean	477.54165	2.06716	341.10117	57.30400	0.04922
Standard Deviation	-----	-----	-----	-----	-----