


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	389.87507	1.19694	278.48220	46.78400	0.02850
Mean	389.87507	1.19694	278.48220	46.78400	0.02850
Standard Deviation	-----	-----	-----	-----	-----