


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	558.84994	3.47868	399.17855	67.06100	0.08283
Mean	558.84994	3.47868	399.17855	67.06100	0.08283
Standard Deviation	-----	-----	-----	-----	-----