


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	443.96658	2.27746	317.11898	53.27500	0.05423
Mean	443.96658	2.27746	317.11898	53.27500	0.05423
Standard Deviation	-----	-----	-----	-----	-----