


Silicone rubber

Tensile test of silicone rubber elastomers



	Extension at Maximum Tensile extension (mm)	Load at Maximum Tensile extension (N)	Tensile strain at Maximum Tensile extension (%)	Time at Maximum Tensile extension (sec)	Tensile stress at Maximum Tensile extension (MPa)
1	433.20008	1.42585	309.42862	51.98300	0.03395
Mean	433.20008	1.42585	309.42862	51.98300	0.03395
Standard Deviation	-----	-----	-----	-----	-----