

Extruded Polystyrene Backer Board



- Waterproof

Closed-cell structure, <0.3% wa
- Lightweight

28-45 kg/m³, easy handling & tr
- Easy to Cut

Score and snap, no special too
- Thermal Insulation

0.028-0.034 W/(m·K) thermal co
- High Strength

150-700 kPa compressive stren
- Custom Sizes

4mm-20mm thickness, tailored

Technical Specifications

Parameter	Value	Standard
Density	28 · 45 kg/m³	ASTM C578 Type IV/X
Compressive Strength	150 · 700 kPa	ASTM D1621 / EN 826
Thermal Conductivity	0.028 · 0.034 W/(m·K)	ASTM C518 / EN 12667
Water Absorption	< 0.3% by volume	ASTM C272 / EN 12087
Dimensional Stability	< 2% @ 70°C	ASTM D2126 / EN 1604
Fire Classification	B1/B2 (EN) / Class A (ASTM)	EN 13501-1 / ASTM E84
Thickness Options	4, 6, 10, 12, 20 mm	Custom available
Sheet Sizes	600×1200, 600×1250, 1200×2400	Custom available
Surface Finish	Smooth, embossed, non-woven	On request
Edge Profile	Square, shiplap, T&G	On request

Packaging & Order Information

- Standard packaging: PE film + pallet, weatherproof export wrapping
- Pallet sizes: 1200×2400mm base, stack height negotiable
- MOQ: 1 pallet (LCL) / 1×20GP container available
- Lead time: 7-15 days from order confirmation (stock dependent)
- Payment terms: T/T 30% deposit, 70% before shipment (flexible for trial orders)
- Incoterms: FOB / CIF / DAP available

Quality & Certifications

ASTM C578	Standard Specification for Rigid, Cellular Polystyrene Thermal Insulation
EN 13164	Thermal insulation products for buildings · Factory made XPS products
CE Marking	CE Marking for XPS Backer Board