


# Rank-1 separation route for LDPE/EVOH/PET

Sequential solvent-targeted recovery at 100 C | minimum step selectivity 11.9%



## Routing logic retained

Each step selects one target polymer and carries the unresolved stream forward to the next step.

Step 1 solvent  
**p-Xylene -> LDPE**  
Sel. 11.9% @100 C

Op. 89.6% @150 C

Step 2 solvent  
**DMSO -> EVOH**  
Sel. 18.4% @100 C

Op. 44.9% @160 C

Final assignment  
**PET -> residue**  
No additional solvent step

Overall path: LDPE -> EVOH -> PET

Solvent labels: p-Xylene = 1,4-dimethylbenzene; DMSO = dimethylsulfoxide. Selectivity values are the operating-step values at 100 C.