


Rank-1 separation route for LDPE/EVOH/PET

Sequential solvent-targeted recovery at 100 C; minimum step selectivity = 11.9%



Stepwise routing evidence

At each step, one polymer is targeted and the unresolved stream continues.

Step	Target	Solvent	Selectivity	Carry-forward
1	LDPE	p-Xylene best: 89.6% @150 C	11.9% @100 C	EVOH + PET
2	EVOH	DMSO best: 44.9% @160 C	18.4% @100 C	PET
3	PET	-- no additional solvent step	residue	complete

Ranked route
LDPE -> EVOH -> PET min sel. 11.9%

Solvent labels: p-Xylene = 1,4-dimethylbenzene; DMSO = dimethylsulfoxide. Values shown are operating-step selectivities at 100 C.